

















Specifications

DESCRIPTION	NORM	DATA
Pile Fiber		100% Polyamide (Solution Dyed)
Gauge		1/10 loop pile
Tuft Density	ISO 1763	168 100 Stitches/m ²
Total Pile Mass	ISO 8543	630 g/m ²
Mass of Pile above the Substrate	ISO 8543	370 g/m ²
Thickness of Pile above the Substrate	ISO 1766	2,75 mm
Surface Pile Density	ISO 8543	0,134 g/cm ³
Total Weight	ISO 8543	3895 g/m ²
Total Thickness	ISO 1765	6,3 mm
Primary Backing		Non-woven primary backing
Backing		Vinyl backing reinforced with glass fiber (100 % recycled PVC)
Tile Size		50x50cm
Tiles per Box		20 = 5m ²
Installation		
Printing Facilities		YES



Technical Performances

RHO-LRV		 Classification EN 1307 - 33 / Commercial Heavy Luxury Class – LC1			
24 Colors	%	 Classement UPEC NF 262 - U3SP3E1C0 (Certificate n° 349T-005.1) Fire rating EN 13501-1: BflS1			
017	9,0%				
019	4,7%				
022*	14,0%				
024	9,9%				
027	8,0%				
028	6,8%				
029	5,8%	Heated Floor  ISO 10456 0,08 m² K/W	Impact Noise Reduction  EN ISO 10143-3 ΔL (w) 24 dB		
034*	17,3%	Electrostatic prop.  ISO 6356 ≤ 2,0kV ISO 10965 RT ≈ 10 ¹⁰ Ω	Sound Absorption  ISO 11654 αw = 0,15 (H)		
037*	11,3%				
041	15,1%				
045	10,6%				
047	9,8%				
049	6,7%	Dimensional Stability  EN 986 ≤ 0,10%	Color Fastness  EN 105 - B02 7/8		
055	18,6%				
062*	20,1%				
075	13,3%				
078	9,9%	 N° 0679-CPR-0196 07 EN 14041: 2004	Castor Chair  EN 985 Passed R≥2,4		
082*	14,6%				
086	14,8%				
095	12,7%				
107	14,9%				
127	16,3%				
138	7,2%				
139	6,3%				



The above information is subject to modifications for the benefit of further improvement. (Updated on 09/02/2017)