

















Specifications

DESCRIPTION	NORM	DATA
Pile Fiber		100% Polyamide (Solution Dyed)
Gauge		1/10 Cut pile
Tuft Density	ISO 1763	205 000 Stitches/m ²
Total Pile Mass	ISO 8543	1200 g/m ²
Mass of Pile above the Substrate	ISO 8543	860 g/m ²
Thickness of Pile above the Substrate	ISO 1766	4,7 mm
Surface Pile Density	ISO 8543	0,183 g/cm ³
Total Weight	ISO 8543	4835 g/m ²
Total Thickness	ISO 1765	8,0 mm
Primary Backing		Non-woven primary backing
Backing		Vinyl backing reinforced with glass fiber (100 % recycled PVC)
Tile Size		50x50cm
Tiles per Box		20 = 5m ²
Installation		
Printing Facilities		YES



Technical Performances

RHO-LRV		 Classification EN 1307 - 23/32 / Commercial General Luxury Class – LC4					
24 Colors	%	Fire rating EN 13501-1: BflS1 					
017	3,2%						
022	13,7%						
024	5,6%						
025	5,6%						
027	2,5%						
028	2,8%						
032	13,2%	Heated Floor  ISO 10456 0,11 m ² K/W		Impact Noise Reduction  EN ISO 10143-3 ΔL (w) 28 dB			
034	12,8%	Electrostatic prop.  ISO 6356 ≤ 2,0kV ISO 10965 RT ≈ 10 ¹⁰ Ω				Sound Absorption  ISO 11654 α _w = 0,20 (H)	
035	7,8%						
043	15,3%	Dimensional Stability  EN 986 ≤ 0,10%				Color Fastness  EN 105 - B02 7/8	
044	11,8%						
047	6,0%	N° 0679-CPR-0198  07 EN 14041: 2004				Castor Chair  EN 985 Passed R<2,4	
048	2,3%						
058	15,6%						
062	29,4%						
085	5,4%						
088	2,4%						
095	7,0%						
098	3,8%						
106	28,9%						
117	2,7%						
135	3,4%						
149	1,3%						
195	6,0%						



The above information is subject to modifications for the benefit of further improvement. (Updated on 24/01/2017)