Mapecoat TNS Multisport Professional

MULTI-LAYERED SYSTEM MADE FROM ACRYLIC RESIN IN WATER DISPERSION FOR MULTI-PURPOSE INDOOR AND OUTDOOR PLAYING SURFACES

Products used for the system:

Mapecoat TNS Line, Mapecoat TNS Color, Mapecoat TNS Finish 1.3.4

and Mapecoat TNS White Base Coat

DESCRIPTION

MAPECOAT TNS MULTISPORT PROFESSIONAL is a multi-layered system made from acrylic resin in water dispersion with selected fillers and is used to make multi-purpose playing surfaces with high resistance to wear, UV rays and various weather

conditions.

MAPECOAT TNS MULTISPORT

PROFESSIONAL may be applied on existing painted surfaces or on new cementitious or asphalt surfaces that need to be dressed.

When MAPECOAT TNS

multisport professional is applied on surfaces it forms a playing surface that has excellent performance characteristics, such as perfect bounce of the ball, quick, safe changes in direction and an excellent compromise between balance and slide for players.

Surfaces dressed with

MAPECOAT TNS MULTISPORT

PROFESSIONAL also have a
very attractive finish and may be
renewed easily and rapidly.

PERFORMANCE AND ADVANTAGES

- · Excellent playing comfort.
- Durable, characterised by high resistance to wear and abrasion from constant foot traffic.
- · Resistant to outdoor conditions.
- Solvent-free and eco-friendly.
- Forms attractive, flat, seamless and highly functional surfaces.
- Quick application, reduces the time required to carry out work and the down time of playing surfaces.
- Wide range of colours available.
- Guarantees an excellent costperformance ratio.

CHEMICAL RESISTANCE

Surfaces dressed with MAPECOAT TNS

MULTISPORT PROFESSIONAL are resistant to:


- · diluted acids;
- alkalis, including 50% sodium hydroxide and detergents normally used for cleaning floors up to a concentration of 20-30%;
- mineral oils, diesel, petrol and kerosene.

COLOURS AVAILABLE

MAPECOAT TNS MULTISPORT PROFESSIONAL is available in 24 different colours from the standard colour chart and personalised colours upon request.

CONSUMPTION RATES

The consumption rates indicated below





Mapecoat TNS Multisport Professional

are for a cycle applied at +15°C to +25°C on a smooth, compact concrete surface. Rougher surfaces and lower temperatures lead to higher consumption rates and longer hardening times. The consumption of MAPECOAT TNS WHITE BASE COAT in particular may vary according to the type of substrate and the planarity of the preparation method used.

MAPECOAT TNS MULTISPORT PROFESSIONAL

average thickness of system 1-1.5 mm

1° layer:

MAPECOAT TNS WHITE BASE COAT

1 kg/m² (one coat)

2° layer:

MAPECOAT TNS FINISH 1.3.4

1 kg/m²

(2 coats)

Finish:

MAPECOAT TNS

COLOR

0.8 kg/m² (2 coats)

N.B.: when applying MAPECOAT TNS PROFESSIONAL on concrete substrates, prime the surface with MAPECOAT I 600 W diluted 1:1 with water at a rate of around 100 g/m², depending on the absorbency of the substrate.

SURFACE PREPARATION

1. Characteristics of the substrate Before applying the **MAPECOAT TNS MULTISPORT PROFESSIONAL**

system, the substrate on which it is to be applied must be carefully analysed. To get the best results, the following must be checked:

- there must be no materials or debris on the substrate which could potentially impede adhesion of the dressing, such as:
 - cement laitance;
 - dust, detached or loose material;
 - protective wax, curing products, paraffin or efflorescence;
 - oil stains or layers of dirty resin;
- traces of paint or chemical products.

Any other kind of material or substance that could affect adhesion of the coating must be removed before starting work. If such materials or substances are present, it is ESSENTIAL that the substrate is prepared using a suitable preparation method. If required, contact MAPEI Technical Services for advice on the most suitable method.

The pull-off strength of the substrate

TECHNICAL DATA OF MAPECOAT TNS FINISH 1.3.4 (after 7 days at +23°C)	
Consistency:	thick liquid
Dry solids content (%):	70
Density (g/cm³):	approx. 1.40
Viscosity of product (mPa·s):	19,000 ± 1,000
Wet abrasion DIN 53778 (cycles):	> 15,000
Taber abrasion test after 7 days at +23°C - 50% R.H. H22 disk, 500 revs/1,000 g (loss by weight):	2.8 g (6%)
Taber abrasion test after 7 days at +23°C - 50% R.H. CS17 disk, 1000 revs (loss by weight):	< 0.1 g (< 1%)
Shore A hardness:	60
Ultimate tensile strength (DIN 53504) after 7 days at +23°C:	0.7 N/mm ²
Elongation at failure (DIN 53504) after 7 days at +23°C:	110%
Change in colour after 1,000 hours exposure to a Weather-Ometer (according to ASTM G 155 cycle 1) - blue: - green: - sky blue: - red: - white:	$\Delta E < 0.8$ $\Delta E < 0.5$ $\Delta E < 0.5$ $\Delta E < 0.5$ $\Delta E < 0.5$
Vapour diffusion resistance coefficient (μ) (ISO 7783/2):	200
Resistance to the passage of vapour of a 0.10 mm thick dry layer $S_{\scriptscriptstyle D}$ (m) (ISO 7783/2):	0.02
Capillary action water absorption coefficient W ₂₄ [kg/(m²·h ^{0.5})] (ISO 1062/3):	0.09
Adhesion to concrete (N/mm²):	2.40

must be more than 1.5 N/mm².

- The substrate must be as flat as possible, and in all cases with a maximum slope of 1.5%.
- For concrete substrates, the maximum moisture content must be not higher than 4% and there must be a suitable vapour barrier. If these conditions are not met the surface must be treated with suitable products. Once treated, make sure the surface is suitable for **MAPECOAT TNS WHITE BASE COAT**, otherwise the coating may detach and/or blisters may form.

MAPECOAT TNS WHITE BASE COAT

may only be applied over other types of acrylic resin-based finishing products after carefully checking that the old finish and MAPECOAT TNS WHITE BASE **COAT** are compatible.

2. Substrate preparation

It is very important that the surface is prepared according to specification to guarantee correct installation and to get the best performance from the **MAPECOAT TNS MULTISPORT** PROFESSIONAL system.

The most suitable method to prepare

concrete surfaces is by shot-blasting or with a diamond disk. All dust must then be removed with a vacuum cleaner. Do not use chemical preparation methods, such as acid rinsing, or aggressive percussion tools, to prevent damaging the substrate. Any defects present, such as holes, pitting, cracking, etc. must be repaired beforehand with **EPORIP**, **MAPEGROUT** or **PLANITOP SMOOTH&REPAIR** depending on the width and depth of the defects and cracks. For asphalt surfaces, we recommend

applying a 3 cm thick bitumen mat made from particles 0 to 6 mm in size. After applying the asphalt mat, we recommend waiting around 10 days before applying **MAPECOAT TNS WHITE BASE COAT** to allow the bitumen to oxidise. Apart from the checks carried out as described in section 1 "Characteristics of the substrate" no other surface preparation is required. Defects such as holes, pitting, cracking, etc. must be repaired with **ADESILEX G19 or MAPEFLEX PB27** depending on the width and depth of the defects and cracks.

3. Preliminary checks before application Make sure that all the checks from

section 1 "Characteristics of the substrate" have been carried out and that all the operations indicated in section 2 "Substrate preparation" have been carried out correctly.

The surrounding temperature must be between +15°C and +30°C and the temperature of the substrate must at least +3°C above the dew-point temperature.

4. Preparation and application of the products

Carefully follow the preparation instructions contained in the Technical Data Sheet for each single product used to form the complete system.

MAPECOAT TNS WHITE BASE COAT, MAPECOAT TNS FINISH

1.3.4, MAPECOAT TNS COLOR and MAPECOAT TNS LINE.

Thickness of system 1-1.5 mm

• First base layer (MAPECOAT TNS WHITE BASE COAT)
Apply MAPECOAT TNS WHITE BASE COAT diluted with 5-10% of clean water, depending on the application method used. Mix the product mixture with a drill at low-speed with a mixing attachment to form a smooth, even paste. Pour the mix prepared according to the indications above onto the surface to be dressed and spread it out in an even layer with a smooth trowel or a rubber spreader.

 Sanding and removing the dust with a vacuum cleaner

When the **MAPECOAT TNS WHITE BASE COAT** has hardened, sand the surface to eliminate any uneven areas from the surface and remove all traces of dust with an industrial vacuum cleaner.

Surface protection (MAPECOAT TNS WHITE BASE COAT)
 Protect the surface just treated with MAPECOAT TNS WHITE BASE COAT against rain, strong air currents.

COAT against rain, strong air currents, high temperatures, falling leaves or other such objects which could damage the surface.

Cleaning

Clean tools used to apply **MAPECOAT TNS WHITE BASE COAT** with clean water. Once dry, traces of the product must be removed mechanically.

 Coating (MAPECOAT TNS FINISH 1.3.4)
 Apply MAPECOAT TNS FINISH

1.3.4 diluted with 10-15% of clean water. Mix with a drill at low-speed with a mixing attachment to form a smooth even paste. Pour the mix prepared according to the indications above onto the surface to be dressed and spread it out evenly and uniformly using a rubber spreader. This cycle requires at least two coats of MAPECOAT TNS FINISH 1.3.4. Wait 12 hours between each coat in normal temperature and humidity conditions.



 Protecting the surface (MAPECOAT TNS FINISH 1.3.4)

Protect the surface just treated with **MAPECOAT TNS FINISH 1.3.4** from rain, strong air currents, high temperatures, falling leaves or other such objects which could damage the surface.

Cleaning

Clean tools used to apply **MAPECOAT TNS FINISH 1.3.4** with clean water. Once dry, traces of the product may only be removed mechanically.

Finish (MAPECOAT TNS COLOR)
 Apply MAPECOAT TNS COLOR
 diluted with 10-15% of water. Mix
 with a drill at low-speed with a mixing
 attachment to form a smooth even
 paste. Pour the mix prepared
 according to the indications above
 onto the surface to be dressed and
 spread it out evenly and uniformly
 using a rubber spreader. This cycle
 requires two coats of MAPECOAT
 TNS COLOR. Wait 12 hours between
 each coat in normal temperature and
 humidity conditions.

 Protecting the surface (MAPECOAT TNS COLOR)

Protect the surface just treated with **MAPECOAT TNS COLOR** from rain, strong air currents, high temperatures, falling leaves or other such objects which could damage the surface.

Cleaning

Clean tools used to apply **MAPECOAT TNS COLOR** with clean water. Once dry, traces of the product may only be removed mechanically.

 Horizontal lines (MAPECOAT TNS LINE)

Apply MAPECOAT TNS LINE directly on dry MAPECOAT TNS COLOR.

Dilute with 10-15% of clean water and mix with a drill at low-speed with a mixing attachment to form a smooth, even paste. Apply the product prepared according to the indications

above with a brush, roller or by spray. To improve the cover of **MAPECOAT TNS LINE**, we recommend applying two coats at 8-12 hours between each coat.

5. Hardening and step-on times At +25°C MAPECOAT TNS FINISH

1.3.4 sets to foot traffic after 12 hours. Wait at least 24 hours after the second coat before allowing vehicles to drive over the surface.

Lower temperatures lead to longer hardening and step-on times.

CLEANING AND MAINTENANCE

Regular cleaning and maintenance operations increase the life of dressed surfaces, improves their appearance and reduces their tendency to collect dirt. Playing surfaces made using the MAPECOAT TNS MULTISPORT PROFESSIONAL system are generally easy to wash with a solution of 5 to 10% neutral or alkali detergent diluted with water. Suitable detergents and cleaning tools are readily available for cleaning this type of surface.

Manufacturers of these detergents supply all the information required on the cleaning procedures to apply. Our Technical Services Department is available for any information required.

NOTE

Procedures regarding the safe handling of the products are contained in the Material Safety Data Sheet for each single product in the system. The use of protective clothing and equipment is recommended when mixing and applying the products.

If the system is applied on different surfaces to those mentioned above, or in climatic conditions and/or for final uses not mentioned in the System Data Sheet, please contact the Technical Services Department at MAPEI S.p.A.

