

Structural Timber Guide 2026

Prolam. Posts

Prolam. Beams

Prolam. PLX Column

Prolam. Fascia

Prolam. PLX20

Prolam. PLX Portal

Prolam. Pergolas

Prolam. Exposed Truss

Prolam®
Engineered Laminated Timber

prolamnz.com

Building better together

Proud to be 100% family-owned Kiwi business

Based in the Tasman, with experience spanning more than 20 years, we design, manufacture and supply glulaminated timber beams and posts for the residential and commercial building industry across New Zealand.

We hope you find this useful, please don't hesitate to get in touch if have any questions.

Prolam Product Range

Product Range 4
Visual Posts 5
Visual Beams 7
Non Visual Beams 10
Fascia 13
PLX20 Beams 14
Exposed Truss 16
Pergolas 17
Finishes 18
PLX Portal 20
PLX Column 22
Prolam Specifier 23
Prolam Sizes and Order Codes 24
Care and Maintenance 28
- Specifications 29
- Durability Statement 30
- Coating Requirements 31
- Checking in Prolam 32
- NZ Timber Design Journal 33

Alternative Charts 34
Span Tables 46
- Timber Properties 47
- Design Data 48
- Producer Statement 48
- Lintel supporting roof & ceiling 49
- Ridge Beam supporting roof & ceiling 50
- Rafter for internal use supporting roof & ceiling 51
- Veranda Rafter (wet use) supporting roof without ceiling 52
- Veranda Rafter (wet use) supporting roof and ceiling 53
- Veranda Lintel (wet use) supporting roof with & without ceiling 54
- Floor Beam supporting joists 55
- Floor Joist PL8 56
- Floor Joist PL12 57
- Deck Bearer supporting deck & cantilever 58
- Deck Joist 59
- Deck Post Bracing Units 60
- Veranda/Carport Bracing Post 61
- Bracing Post Veranda/Carport - free standing supporting roof & ceiling PL8 62
- Bracing Post Veranda/Carport - free standing supporting roof & ceiling PL12 63
- Bracing Post Veranda/Carport - attached to house supporting roof & ceiling PL8 64
- Bracing Post Veranda/Carport - attached to house supporting roof & ceiling PL12 65
- Non-Bracing Post - attached to the house supporting veranda roof & ceiling only 66
- Non-Bracing Post - attached to the house supporting veranda or deck floor only 67
- Non-Bracing Post - attached to house supporting veranda deck floor & roof ceiling 68

Fixings 69
- Fixing to MCA Timber 70
- Tapered Ceiling Beam Detail 71
- Support for Bricks 72
- Post Fixings 73
- Corner Post Fixings 75
- PLX20 Fixings 76

Stud Requirement Table 78
Holes in Laminated Timber 79
FAQs 80
Building Product Information 85
Licensed Builders Practitioner Details 86

Prolam® Product Range

Prolam® Posts

Prolam® PLX20

Prolam® Pergolas

Prolam® Beams

Prolam® Fascia

Prolam® Exposed Truss

Prolam® PLX Portal

Prolam® PLX Column



Visual Posts

Standard lengths:	2.4, 2.7, 3.0, 3.6, 4.2, 4.8, 5.4, 6.0, 6.6, 7.2
Grade:	Visual / Appearance A Finger Jointed
Structural grade:	PL8 and PL12
Treatment:	MCA H5 KD
Finishes:	Machined Bandsawn (less 3mm per side) Sanded & Sealed Pre-Primed Square Edge
Advantages:	H5 Posts Codemark Certified Do not need post brackets Gives you bracing units (Tables 11&12) Structurally Stable Superior Fire Resistance Good load carrying capacity Won't twist or warp FSC options available
Common Uses:	Verandas Pergolas Fences Decks Entranceways Carports

Visual/Appearance A H5 KD Posts

PLP – Prolam® Post

CodeMark




Pre-primed Finish | Visual Machine Finish | Bandsawn Finish | Sanded & Sealed Finish

Code	Size
PLPH5-100	88 x 88mm
PLPH5-125	112 x 112mm
PLPH5-150	135 x 135mm
PLPH5-200	180 x 180mm
PLPH5-250	220 x 220mm
PLPH5-300	260 x 260mm
PLPH5-350	300 x 300mm
PLP12H5-100	88 x 88mm
PLP12H5-125	112 x 112mm
PLP12H5-150	135 x 135mm
PLP12H5-200	180 x 180mm
PLP12H5-250	220 x 220mm
PLP12H5-300	260 x 260mm
PLP12H5-350	300 x 300mm

Visual/Appearance A Beams 88mm

PLVL – Prolam® Visual Lintel
PL8, PL12, H5, H3.2KD, H1.2KD



Larger sizes available: 360mm, 405mm, 450mm, 495mm, 540mm, 595mm

Refer to pages 24-27 for product codes.

Standard lengths: 3.6, 4.2, 4.8, 5.4, 6.0, 6.6, 7.2 (m) - H3.2 and H1.2

Other lengths: 7.8, 8.4, 9.0, 9.6, 10.2, 10.8, 11.4, 12.0 (m) - H3.2/H5 only

Grade: Visual / Appearance A Finger Jointed


Structural grade: PL8, PL12

Treatment: MCA H3.2/H5 KD, H1.2 KD

Finishes: Machined
Sanded & Sealed
Bandsawn (less 3mm each side)
Primed

Visual/Appearance A Beams 63mm

PLVL – Prolam® Visual Lintel
PL8, PL12, H5KD, H3.2KD, H1.2KD



Larger sizes available: 360mm, 405mm, 450mm, 495mm, 540mm, 595mm


Refer to pages 24-27 for product codes.

Uses:
- Veranda Lintels
- Rafters and Beams
- Pergola Beams and Rafters

Advantages:
- Exterior treatment
- Structurally Stable
- Won't twist or warp
- Aesthetically pleasing
- FSC options available

Visual/Appearance A Beams 42mm

PLVL – Prolam® Visual Lintel
PL8, PL12, H5KD, H3.2KD, H1.2KD




Larger sizes available: 360mm, 405mm, 450mm

Refer to pages 24-27 for product codes.

Uses:
- Veranda Lintels, Rafters and Beams
- Pergola Beams and Rafters
- Deck Joists
- Ceiling Rafters
- Carport Rafters

Non-Visual Beams 90mm

PL – Prolam® Lintel
PL8, PL12, H5KD, H3.2KD, H1.2KD



Larger sizes available: 360mm, 405mm, 450mm, 495mm, 540mm, 595mm


Refer to pages 24-27 for product codes.

Standard lengths:	3.6, 4.2, 4.8, 5.4, 6.0, 6.6, 7.2
Grade:	Non-visual, Utility
Structural grade:	PL8 / PL12
Treatment:	MCA H3.2/H5 KD, H1.2 KD
Finishes:	Dressed
Other lengths:	7.8, 8.4, 9.0, 9.6, 10.2, 10.8, 11.4, 12.0 (only in H3.2 NV)
Species:	Radiata, Douglas Fir

All non-visual beams are supplied precambered.

Non-Visual Beams 63mm

PL – Prolam® Lintel
PL8, PL12, H5KD, H3.2KD, H1.2KD



Larger sizes available: 360mm, 405mm, 450mm, 495mm, 540mm, 595mm

Refer to pages 24-27 for product codes.


Uses:

- Garage Door Lintels
- Deck Bearers
- Deck Joists
- Floor Joists
- Rafters
- Framing Lintels
- Ridge Beams

All non-visual beams are supplied precambered.

Non-Visual Beams 42mm

PL – Prolam® Lintel
PL8, PL12, H5KD, H3.2KD, H1.2KD




Larger sizes available: 360mm, 405mm, 450mm

Refer to pages 24-27 for product codes.

All non-visual beams are supplied precambered.

Fascia

H3.2KD



Custom surface rebate

Fascia Width _____

Fascia Thickness _____

Rebate Height _____

Rebate Width _____


Treatment:	MCA H3.2 KD NST
Finish:	Dressed
Lengths:	4.8, 5.4, 6.0m
Other sizes:	Made to order
Advantages:	Exterior treatment Premium finish
Minimum width:	30mm

Prolam PLX20® Beams

PLX – Prolam® Hybrid Lintel

Strength, stability and sustainability

The innovative Prolam PLX20 beam provides superior support for today's build from design to installation.Precision engineered from quality New Zealand pine, the PLX20 has steel laminated in the top and bottom laminates for extra strength and stiffness. It allows a small member beam to span further, making it ideal for garage lintels and other wide structures.



- High strength and durability for greater spanning.
- Sustainable option with high timber to steel ratio.
- Easy to specify using the Prolam Specifier.
- Competitively priced.
- Up to 40% lighter than alternatives for fast and easy installation.



Prolam PLX20® Beams

Sizes (mm): 240x90, 290x90

Product Code: PLX20H1-250100, PLX20H1-300100

Available Lengths: 3.6, 4.2, 4.8, 5.4, 6.0, 6.6 (m)

Treatment: H1.2 KD

Grade: Non-Visual

Species: Radiata Pine

Applications: Lintels, Rafters, Floor beams Ridge beams

Beam Length (m)	Steel Length (m)	Steel Set Back (mm)
3.6	3.2	200
4.2	3.6	300
4.8	4.2	300
5.4	4.7	350
6.0	5.3	350
6.6	6.0	300

Scan to learn more


Structural Properties

	Characteristic Strengths (MPa)				Elastic Moduli (MPa)	
	Bending	Tension parallel to grain	Shear in Beam	Compression parallel to grain	Short modulus of elasticity parallel to the grain	Short duration modulus of rigidity for beams
PLX20-250100 240 x 90mm	40	4	3.7	18	20000	480
PLX20-300100 290 x 90mm	45	4	3.7	18	21000	480

Notes
1. Intended for use as a beam and not as tension or compression member.
2. Bending strength and MoE have been determined from testing. Other properties are based on SG6 timber.
3. Beam design to be in accordance with NZ3603 assuming a timber member using appropriate factors (eg $\phi = 0.8$).
4. k_2 factor for creep deflection = 1.25.
5. Joint group J5 for design of connections.

Fixing Options

Refer to pages 76-77 for further fixing details.



All non-visual beams are supplied precambered.

Avoid drilling through or damaging the steel bar for fixings and take care to prevent the steel plate from damaging the screw threads.

Exposed Truss

A stand-out solution inside and out

Prolam Exposed Trusses blend the beauty and strength of timber with the structural integrity and stability of our glulam solution. Our streamlined process, from design to supply, simplifies integration into residential and commercial construction. Choose from standard profiles or customized sizes and designs to match your needs.

- Premium visual grade structural timber with FSC options available
- Variety of finishes available
- H1.2 and H3.2 Treatments available for interior & exterior use
- Easy to specify with PS1 certification
- Expert advice from in-house structural engineers
- High dimensional stability (no twisting or warping)

Scan to learn more



Pergolas

Need a Pergola? Think Prolam.

Pergolas enhance the style, depth, and shade of homes and outdoor areas and with Prolam pergolas, the elegance of timber is seamlessly combined with the structural reliability of glulam. Crafting and erecting pergolas with Prolam posts and beams is straightforward and easy thanks to our user-friendly process.

- PL8 & PL12 structural grades readily available
- Premium quality and dimensional stability (no twisting or warping)
- MCA H3.2 & H5 treatment for exterior use
- Available in a wide range of sizes and lengths
- Variety of finishes available
- Expert advice from in-house structural engineers
- Premium visual grade timber with FSC options available

Scan to learn more



Prolam® Finishes


Visual - Appearance A

This grade is intended for use in applications where appearance of the member is important and clear or painted finishes are used. All surface voids are filled, small tight knots are permitted. The surfaces are planer machined to a high quality finish.



Non-Visual H3.2 - Appearance C

This grade is intended for use in applications where appearance is unimportant. All appearance blemishes are permitted in this grade. The surfaces are machined, but machine skip is permissible and blemishes, voids and manufacturing will remain unrepaired. Loose, knots, wane, pith and open knot holes may be present.



Non-Visual H1.2 - Appearance C

This grade is intended for use in applications where appearance is unimportant. H1.2 treatment is colour coded pink. All blemishes are permitted in this grade. The surfaces are machined, but skip is permissible, and blemishes, voids and manufacturing will remain unrepaired. Loose knots, wane, pith and open knot holes may be present.



Please email info@prolamnz.com if you would like to request samples.

Visual H1.2 - Appearance A

This grade is intended for use in applications where appearance of the member is important and clear or painted finishes are used. All surface voids are filled, small tight knots are permitted. The surfaces are planer machined to a high quality finish. The yellow tint fades quickly.



Bandsawn

This is only supplied in the visual grade, as it is used for rustic visual appearance, the "roughness" of the bandsawn finish may vary slightly between batches. This product must be sealed as per our sealing specifications.



Sanded and sealed

This is a premium finish added to a visual product, where all blemishes are filled, the whole product is sanded and then coated with a sealer that will protect the product from ingress of moisture for 6-8 weeks. This sealer is not a long term sealer. The product must be sealed for the long term as per our sealing specifications.



Preprimed


This is a primary coat that is applied in our factory as a protective coat to stop ingress of moisture until the undercoat and top coats are applied. This primer coat is not to be used as the final finish and the product must be sealed for the long term as per our sealing specifications.



Part of the **PLX Bracing** range

Prolam PLX Portal®

PLX Bracing Portal System




The next generation in portal bracing is here!

A strong but lightweight timber bracing solution, the PLX Portal is constructed from three glulam timber elements, including the trademarked PLX20 Beam. The reinforced beam offers excellent spanning capability to deliver optimal design flexibility for architectural features ranging from large internal openings to garage and window bracing portals or anywhere you need bracing but only have a narrow wall space.



- High strength and durability.
- Up to 40% lighter than steel portals.
- Fast installation – no extra equipment or staff.
- Better insulation values than steel.
- Competitively priced.
- Specify with a free PS1 on the Prolam Specifier.



Prolam PLX Portal®

Scan to learn more

PLX200 Portal Series Bracing Capacity - (Leg Size 360x90mm)

Nominal Stud Height (m)	Max. Opening Height (m)	Max. Opening Width (m)	Wind Bracing (BU's)	Earthquake Bracing (BU's)
2.4	2.1	6.0	184	202
2.7	2.4	6.0	180	199
3.0	2.7	6.0	176	195

PLX150 Portal Series Bracing Capacity - (Leg Size 240x90mm)

Nominal Stud Height (m)	Max. Opening Height (m)	Max. Opening Width (m)	Wind Bracing (BU's)	Earthquake Bracing (BU's)
2.4	2.1	6.0	108	135
2.7	2.4	6.0	96	120
3.0	2.7	6.0	87	108

Refer to the PLX Portal Design Guide for full bracing capacity charts and product codes.



Prolam PLX Column


Scan to learn more


Part of the **PLX Bracing** range

A powerful bracing solution for open-plan designs

Delivering up to 130 bracing units in a single glulam member, the PLX Column is a space-saving, space-making solution for today's homes. Available in 400mm x 90mm or 360mm x 90mm sizes, its compact footprint and high bracing capacity in minimal wall lengths allows you to create wider openings, cleaner lines and more light-filled, liveable interiors. Ideal for open plan living areas, kitchens, entryways, wing walls and large openings.

- Angled anchors for edges of insulated foundations
- Delivered as a prefabricated kitset ready to install
- Cut to length on site for an exact fit
- Connects easily to timber members (no packing needed)
- Lightweight and easy to install
- Simple to specify with a Producer Statement
- A sustainable choice – made from NZ plantation grown pine
- NZ-made innovation





Code	Description	Column Size (mm x mm)	Column Height (m)	Wind BU	Earthquake BU
PLXCH1-400100-2.4H	Prolam PLX Column 360x90 H1.2 2.4H	360 x 90	Up to 2.4	91	103
PLXCH1-400100-2.7H	Prolam PLX Column 360x90 H1.2 2.7H		2.7	81	91
PLXCH1-400100-3.0H	Prolam PLX Column 360x90 H1.2 3.0H		3	73	82
PLXCH1-450100-2.4H	Prolam PLX Column 400x90 H1 2 2.4H	400 x 90	Up to 2.4	116	131
PLXCH1-450100-2.7H	Prolam PLX Column 400x90 H1.2 2.7H		2.7	103	117
PLXCH1-450100-3.0H	Prolam PLX Column 400x90 H1.2 3.0H		3	93	105

The Prolam® Specifier

Specify with certainty.

The Prolam Specifier is an efficient and reliable tool for designing structural timber elements. It covers a wide range of most common structural members.

The specifier allows users to effortlessly design members with spans and loaded dimensions beyond the scope of NZS3604.

- Professionally designed for ultimate user experience
- Optimized for mobile
- Clear quality content
- Training is available
- Generates PS1 Certificate

Scan to learn more



Design service and design assistance available for:

- Exposed trusses
- Complex beams for Alfresco areas
- Lintels and posts
- Bracing portals for Raking portals
- And more

Scan to learn more

Prolam Sizes and Order Codes

Posts Visual - PL8 H5 MCA

Width & Thickness

	88	112	135	180	220	260	300
Code	PLPH5-100	PLPH5-125	PLPH5-150	PLPH5-200	PLPH5-250	PLPH5-300	PLPH5-350

Posts Visual - PL12 H5 MCA

Width & Thickness

	88	112	135	180	220	260	300
Code	PLP12H5-100	PLP12H5-125	PLP12H5-150	PLP12H5-200	PLP12H5-250	PLP12H5-300	PLP12H5-350

Beam Visual - PL8 H3.2 MCA

Width & Thickness

		140	190	240	290	315
42	**Code**	PLVL8H3-15050	PLVL8H3-20050	PLVL8H3-25050	PLVL8H3-30050	PLVL8H3-35050
63	**Code**	PLVL8H3-15075	PLVL8H3-20075	PLVL8H3-25075	PLVL8H3-30075	PLVL8H3-35075
88	**Code**	PLVL8H3-150100	PLVL8H3-200100	PLVL8H3-250100	PLVL8H3-300100	PLVL8H3-350100
112	**Code**	PLVL8H3-150125	PLVL8H3-200125	PLVL8H3-250125	PLVL8H3-300125	PLVL8H3-350125
135	**Code**	PLVL8H3-150150	PLVL8H3-200150	PLVL8H3-250150	PLVL8H3-300150	PLVL8H3-350150

Beams Visual - PL12 H3.2 MCA


Width and Thickness

		140	190	240	290	315
42	**Code**	PLVL12H3-15050	PLVL12H3-20050	PLVL12H3-25050	PLVL12H3-30050	PLVL12H3-35050
63	**Code**	PLVL12H3-15075	PLVL12H3-20075	PLVL12H3-25075	PLVL12H3-30075	PLVL12H3-35075
88	**Code**	PLVL12H3-150100	PLVL12H3-200100	PLVL12H3-250100	PLVL12H3-300100	PLVL12H3-350100
112	**Code**	PLVL12H3-150125	PLVL12H3-200125	PLVL12H3-250125	PLVL12H3-300125	PLVL12H3-350125
135	**Code**	PLVL12H3-150150	PLVL12H3-200150	PLVL12H3-250150	PLVL12H3-300150	PLVL12H3-350150

Product codes

Product codes are usually the following sequence (with PLX20 and PLX Portal being exceptions):

Example code: **PLVL8H3-300100**





Beam Visual - PL8 H3.2 MCA

Width and Thickness

360	405	450	495	540	595
PLVL8H3-40050	PLVL8H3-45050	PLVL8H3-50050	PLVL8H3-55050	PLVL8H3-60050	PLVL8H3-65050
PLVL8H3-40075	PLVL8H3-45075	PLVL8H3-50075	PLVL8H3-55075	PLVL8H3-60075	PLVL8H3-65075
PLVL8H3-400100	PLVL8H3-450100	PLVL8H3-500100	PLVL8H3-550100	PLVL8H3-600100	PLVL8H3-650100
PLVL8H3-400125	PLVL8H3-450125	PLVL8H3-500125	PLVL8H3-550125	PLVL8H3-600125	PLVL8H3-650125
PLVL8H3-400150	PLVL8H3-450150	PLVL8H3-500150	PLVL8H3-550150	PLVL8H3-600150	PLVL8H3-650150

Beams Visual - PL12 H3.2 MCA


Width and Thickness

360	405	450	495	540	595
PLVL12H3-40050	PLVL12H3-45050	PLVL12H3-50050	PLVL12H3-55050	PLVL12H3-60050	PLVL12H3-65050
PLVL12H3-40075	PLVL12H3-45075	PLVL12H3-50075	PLVL12H3-55075	PLVL12H3-60075	PLVL12H3-65075
PLVL12H3-400100	PLVL12H3-450100	PLVL12H3-500100	PLVL12H3-550100	PLVL12H3-600100	PLVL12H3-650100
PLVL12H3-400125	PLVL12H3-450125	PLVL12H3-500125	PLVL12H3-550125	PLVL12H3-600125	PLVL12H3-650125
PLVL12H3-400150	PLVL12H3-450150	PLVL12H3-500150	PLVL12H3-550150	PLVL12H3-600150	PLVL12H3-650150

Product codes

Product codes are usually the following sequence (with PLX20 and PLX Portal being exceptions):

Example code: **PLVL8H3-300100**



Beams Non-Visual - PL8 H3.2 MCA

Width & Thickness

		140	190	240	290	315
42	Code	PL8H3-15050	PL8H3-20050	PL8H3-25050	PL8H3-30050	PL8H3-35050
63	Code	PL8H3-15075	PL8H3-20075	PL8H3-25075	PL8H3-30075	PL8H3-35075
88	Code	PL8H3-150100	PL8H3-200100	PL8H3-250100	PL8H3-300100	PL8H3-350100
112	Code	PL8H3-150125	PL8H3-200125	PL8H3-250125	PL8H3-300125	PL8H3-350125
140	Code	PL8H3-150150	PL8H3-200150	PL8H3-250150	PL8H3-300150	PL8H3-350150

Non-Visual Beams - PL12 H3.2 MCA

Width & Thickness

		140	190	240	290	315
42	Code	PL12H3-15050	PL12H3-20050	PL12H3-25050	PL12H3-30050	PL12H3-35050
63	Code	PL12H3-15075	PL12H3-20075	PL12H3-25075	PL12H3-30075	PL12H3-35075
88	Code	PL12H3-150100	PL12H3-200100	PL12H3-250100	PL12H3-300100	PL12H3-350100
112	Code	PL12H3-150125	PL12H3-200125	PL12H3-250125	PL12H3-300125	PL12H3-350125
140	Code	PL12H3-150150	PL12H3-200150	PL12H3-250150	PL12H3-300150	PL12H3-350150

Non-Visual Beams - PL12 H3.2

Width and Thickness

		140	190	240	290	315
42	Code	PL8H1-15050	PL8H1-20050	PL8H1-25050	PL8H1-30050	PL8H1-35050
63	Code	PL8H1-15075	PL8H1-20075	PL8H1-25075	PL8H1-30075	PL8H1-35075
88	Code	PL8H1-150100	PL8H1-200100	PL8H1-250100	PL8H1-300100	PL8H1-350100
140	Code	PL8H1-150150	PL8H1-200150	PL8H1-250150	PL8H1-300150	PL8H1-350150

Non-Visual Beams - PL12 H1.2

Width and Thickness

		140	190	240	290	315
42	Code	PL12H1-15050	PL12H1-20050	PL12H1-25050	PL12H1-30050	PL12H1-35050
63	Code	PL12H1-15075	PL12H1-20075	PL12H1-25075	PL12H1-30075	PL12H1-35075
88	Code	PL12H1-150100	PL12H1-200100	PL12H1-250100	PL12H1-300100	PL12H1-350100
140	Code	PL12H1-150150	PL12H1-200150	PL12H1-250150	PL12H1-300150	PL12H1-350150

Product codes

Product codes are usually the following sequence (with PLX20 and PLX Portal being exceptions):

Example code: **PLVL8H3-300100**



Beams Non-Visual - PL8 H3.2 MCA

Width & Thickness

360	405	450	495	540	595
PL8H3-40050	PL8H3-45050	PL8H3-50050	PL8H3-55050	PL8H3-60050	PL8H3-65050
PL8H3-40075	PL8H3-45075	PL8H3-50075	PL8H3-55075	PL8H3-60075	PL8H3-65075
PL8H3-400100	PL8H3-450100	PL8H3-500100	PL8H3-550100	PL8H3-600100	PL8H3-650100
PL8H3-400125	PL8H3-450125	PL8H3-500125	PL8H3-550125	PL8H3-600125	PL8H3-650125
PL8H3-400150	PL8H3-450150	PL8H3-500150	PL8H3-550150	PL8H3-600150	PL8H3-650150

Non-Visual Beams - PL12 H3.2 MCA

Width & Thickness

360	405	450	495	540	595
PL12H3-40050	PL12H3-45050	PL12H3-50050	PL12H3-55050	PL12H3-60050	PL12H3-65050
PL12H3-40075	PL12H3-45075	PL12H3-50075	PL12H3-55075	PL12H3-60075	PL12H3-65075
PL12H3-400100	PL12H3-450100	PL12H3-500100	PL12H3-550100	PL12H3-600100	PL12H3-650100
PL12H3-400125	PL12H3-450125	PL12H3-500125	PL12H3-550125	PL12H3-600125	PL12H3-650125
PL12H3-400150	PL12H3-450150	PL12H3-500150	PL12H3-550150	PL12H3-600150	PL12H3-650150

Non-Visual Beams - PL12 H3.2

Width and Thickness

360	405	450	495	540	595
PL8H1-40050	PL8H1-45050	PL8H1-50050	PL8H1-55050	PL8H1-60050	PL8H1-65050
PL8H1-40075	PL8H1-45075	PL8H1-50075	PL8H1-55075	PL8H1-60075	PL8H1-65075
PL8H1-400100	PL8H1-450100	PL8H1-500100	PL8H1-550100	PL8H1-600100	PL8H1-650100
PL8H1-400150	PL8H1-450150	PL8H1-500150	PL8H1-550150	PL8H1-600150	PL8H1-650150

Non-Visual Beams - PL12 H1.2

Width and Thickness

360	405	450	495	540	595
PL12H1-40050	PL12H1-45050	PL12H1-50050	PL12H1-55050	PL12H1-60050	PL12H1-65050
PL12H1-40075	PL12H1-45075	PL12H1-50075	PL12H1-55075	PL12H1-60075	PL12H1-65075
PL12H1-400100	PL12H1-450100	PL12H1-500100	PL12H1-550100	PL12H1-600100	PL12H1-650100
PL12H1-400150	PL12H1-450150	PL12H1-500150	PL12H1-550150	PL12H1-600150	PL12H1-650150

Product codes

Product codes are usually the following sequence (with PLX20 and PLX Portal being exceptions):

Example code: **PLVL8H3-300100**



Care & Maintenance



Specifications

Storage and Handling

Storage and handling of Prolam® is the same as any dry timber. As timber naturally absorbs moisture from surrounding environment, exposure to wet weather will dimensionally change the product and cause cracking. The end grain of timber is particularly vunerable. Stack on level bearers, 150 mm minimum clear of the ground. Store under cover to keep dry prior to installation. Keep unsealed product wrapped. Also refer to Prolam Sealing Specifications.

Inground Use

When using posts inground, it's recommended the portion of the post that goes in the ground should be sealed to prevent the post taking up moisture and help prevent cracking of the concrete around the post. Also refer to Prolam Sealing Specifications.

No Substitutions

Substitutions are not permitted to any specified Prolam products or associated components or accessories. The structural properties of other manufactures laminated products may not be comparable.

Description

Prolam® is engineered,laminated timber with unsurpassed performance, using MCA H5 and H3.2, H1.2 treatments means it can be used in almost any situation. Prolam is made to standards AS/NZS 1328.1 and AS/NZS 1491 and treated to NZS 3640. Using Prolam elimates the wide variations in solid timber, and allows wide openings to be spanned with ease, along with keeping the lintel depth to a minimum. Prolam is available in many different sizes/grades, meaning there is a beam for every application.

Design Criteria

Prolam is designed to comply with AS/NZS 1170.0, .1, .2, .3, and .5, structural design actions, NZS3603 Timber Structures, and to comply with the NZBC.



Durability Statement

Prolam® products are manufactured to the requirements of AS/NZS 1328.1:1998, under an approved quality system based on the 1S0 9000 series of standards. As such if the product is used in accordance with Prolam product literature, it will meet the durability clauses of the New Zealand Building Code B2.

Subfloor Applications

- Prolam may be used where approved practices for clearance and ventilation are used.

External Use

- Prolam is recommended for weather exposed applications if sealed and maintained in accordance with Prolam Sealing Specifications.

Preservative Treatment

- Prolam Beams are MCA H3.2 or H1.2 treated as defined by NZS 3640:2011, H3.2 must be used for weather exposed applications, such as Veranda beams, deck bearers, and subfloor applications.
- Prolam Posts are MCA H5 treated as defined by NZS 3640:2011 for in-ground and weather exposed applications, such as deck piles, Veranda posts and similar applications.

Storage of Prolam

- To ensure Prolam remains straight and true at the time of installation, follow the below recommendations:
  1. Store under cover so that it remains dry until installation.
  2. Stack clear of the ground for good ventilation.
  3. Stack on bearers to keep flat and straight.

Branded Prolam

- Prolam is branded for your protection. Lookalike materials may not perform to the same standard.
- For your protection do not accept unauthorized substitution

Coating requirements

For Prolam products that are exposed or in-ground

All Prolam products must be coated correctly. This is essential to ensure ongoing performance (durability) as well as maintaining the appearance, where appearance is important. Compliance with all Prolam requirements, including coating requirements, is a condition of our warranty.

Instructions

These instructions apply where the product is exposed as defined in Figure 4.3(b) of NZS 3604:2011 below.

Mandatory requirements

For Prolam products that will be exposed to moisture:

- All exposed surfaces must be fully coated within 14 days of installation.
- All exposed surfaces, cut ends and joints must be sealed with a good quality stain or alkyd primer. Allow to dry as per manufacturer/ supplier instructions.

For paint:

- Apply a single enamel undercoat and then apply two full topcoats compatible with the undercoat.
- Painting is to be carried out in accordance with best practice: 1 x undercoat and 2 x topcoats to achieve a total DFT (dry film thickness) of 80 microns (comprised of undercoat DFT 30 microns, topcoat DFT 25 microns/coat).
- Prowood recommends only light-coloured paints, but where a dark colour is selected it must have a light reflectance value (LRV) of greater than 45 %.
- Recoating requirements are in accordance with the manufacturer/supplier instructions.

For stain:

- Apply three coats of premium oil-based stain to all exposed surfaces including cut ends and joints.
- Prowood recommends only light coloured stains.
- Prowood recommends CD50X or Dryden's Penetrating Wood Oil.

For further information

For our handling and storage requirements and for our warranty refer to: **www.prolamnz.com/technical**

Optional requirements

For Prolam products where maintenance of the appearance applies:

- Fill and sand any damage e.g., depressions, temporary fixing holes or unintended transport damage.
- Holes or large imperfections can be filled with a timber plug using an exterior glue.
- Sand the product until the surface is smooth and completely free from dirt and dust.
- Coat as above.

For Prolam posts that are to be installed in-ground:

It is recommended the in-ground portion of the Prolam post should also be coated before installation to ensure posts do not absorb moisture prior to the concrete curing.
Painting as detailed above is recommended.




Fig 4.3(a &b) NZS 3604:2011

Checking in Prolam

One of the advantages of glued laminated timber construction is that while seasoning checks may occur for the same reasons that they do in sawn members, checking in glued laminated timber will generally occur to a much lesser degree because of careful control of the moisture content of timber used for laminating.

Checks in wood are separations along the fibres normally occurring across the rings of annual growth resulting from stresses developed during changes in moisture content. Checks in glued laminated timber may appear as openings parallel to the grain on the sides of members. As wood loses moisture to the surrounding atmosphere, the outer fibres of the member lose moisture at a more rapid rate than do the inner fibres.


As outer fibres try to shrink, they are restrained by the inner portion of the member that has higher moisture content. The more rapid the rate of drying, the greater will be the differential in shrinkage between the outer and inner fibres resulting in higher shrinkage stresses. These resultant stresses perpendicular to the grain of the wood can cause characteristic wood seasoning checks. The influence of checks on the structural performance of glued laminated timber members is generally minor. Checking can be minimised by careful installation practices that avoid prolonged exposure of the members during construction.

Identification of Checking

Checks occur as transverse separations or openings that are nearly parallel to the grain direction in glued laminated timber and generally follow the grain direction around knots and along sloping grain.

Differences in the shrinkage rate of individual laminations used is glued laminated timber tend to concentrate shrinkage stresses at or near glue lines, resulting in checks. Checks are often confused with delamination that occurs when the glue bond is not adequate.

The presence of wood fibre separation in these openings is the key distinguishing characteristic of seasoning checks. Openings due to inadequate adhesive bonding may appear as smooth wood surface separations, possibly darkened by the adhesive film, or as glossy surface areas of adhesive with an absence of torn wood fibres.



NZ Timber Design Journal **Exposed**

Extract from Issue 2 – Volume 8

It can be assumed that stresses will develop along glue-lines in exposed glulam, simply because the grain orientation, ring orientation, wood density, response to moisture etc. thus will differ between adjacent laminations. European specifications for exposed glulam state that the growth rings in the laminations must all be oriented the same way, and they show a diagram of flat-sawn laminations all with the pith-side downwards.

This is hardly practical in New Zealand with Radiata as the ring orientation is likely to change across a finger joint, and many laminations will be quarter-sawn, flat sawn and everything in between.

Therefore delamination is to be expected but generally should not penetrate more than 20 mm in properly cured glulam, made with resorcinol adhesive. Exposed treated solid timber is likely to develop similar checking. The reason for this is that the moisture fluctuations that give rise to the stresses do not penetrate far, i.e. they are damped out by the resistance of the wood to diffusion of moisture.

Forest Research has tested glulam from a cool store that showed obvious delamination. There appeared to be little effect on strength unless the delamination goes right through. There have been experiments to determine how much delamination can be tolerated before an effect on shear is noticed. Where the glue-line was artificially narrowed by placing adhesive tape along the laminations prior to gluing, there was no effect down to 25% of the width remaining. When the glued area was reduced by placing adhesive strips across the wood at intervals, an immediate effect was noticed. It all has to do with the stress-raisers generated by the delamination.

Some type of sealing is certainly helpful, and painting is excellent but it must be maintained. An oil-based preservative such as creosote is effective because the oiliness acts as a water repellent. I have seen a thick tacky substance applied to glulam bridge stringers, same as can be applied to steel as a rust preventative.

The bridge in question is at the entrance to the Whakarewarewa village in Rotorua and is still giving good service after 40 years. There are several proprietary formulations of water repellent sealants on the market, and some manufacturers apply “Ensele” as a matter of course.

Written by Bryan Walford, Forest Research Institute, Rotorua



Alternative Charts



Alternative to hy90

Prolam® sizes are based on equivalent defection. These tables are for guidance only, and any Prolam substitution should be verified against the complete selection chart or the Prolam online specifier. specifier.prolamnz.com Alternatives may not be suitable for all situations.

hy90 E = 9.5GPa	Prolam PL8 Alternative	Prolam PL12 Alternative	Prolam PLX20 * Alternative
150 x 90	190 x 63	140 x 88	-
200 x 90	240 x 63	190 x 88	-
240 x 90	290 x 63	240 x 88	-
300 x 90	360 x 63	290 x 88	240 x 90
360 x 90	405 x 88	360 x 88	290 x 90
400 x 90	450 x 88	405 x 88	-

* Available in 3.6m, 4.2m, 4.8m, 5.4m, 6.0m lengths

Alternative to hyONE (LVL16)

Prolam sizes are based on equivalent defection. These tables are for guidance only, and any Prolam substitution should be verified against the complete selection chart or the Prolam online specifier. specifier.prolamnz.com. Alternatives may not be suitable for all situations.

hyONE E = 16GPa	Prolam PL8 Alternative	Prolam PL12 Alternative	Prolam PLX20 * Alternative
240 x 90	315 x 88	290 x 88	240 x 90
300 x 90	405 x 88	360 x 88	290 x 90
360 x 90	495 x 88	405 x 88	-
400 x 90	540 x 88	450 x 88	-

* Available in 3.6m, 4.2m, 4.8m, 5.4m, 6.0m lengths

This table applies only to Prolam products.

Alternative to Hyne 17c Glulam

Prolam® sizes are based on equivalent defection. These tables are for guidance only, and any Prolam substitution should be verified against the complete selection chart or the Prolam online specifier. specifier.prolamnz.com. Alternatives may not be suitable for all situations.

Hyne 17c E = 16.7GPa	Prolam PL8 Alternative	Prolam PL12 Alternative
130 x 65	190 x 63	190 x 42 or 140 x 88
165 x 65	240 x 63 or 190 x 88	190 x 63
195 x 65	240 x 88 or 290 x 42	240 x 63
230 x 65	290 x 88	240 x 88
245 x 65	315 x 63 or 290 x 88	290 x 63
260 x 65	315 x 88	315 x 63 or 290 x 88
295 x 65	360 x 88	315 x 88 or 405 x 42
330 x 65	405 x 88	405 x 63
360 x 65	450 x 88	450 x 63
395 x 65	495 x 88	405 x 88
425 x 65	495 x 88	450 x 88
525 x 65	N/A	540 x 88
295 x 85	405 x 88	360 x 88
330 x 85	450 x 88	405 x 88
360 x 85	495 x 88	405 x 88
425 x 85	540 x 88	495 x 88
460 x 85	595 x 88	540 x 88
525 x 85	N/A	595 x 88

This table applies only to Prolam products.

Alternative to hySPAN or LVL13

Prolam® sizes are based on equivalent defection. These tables are for guidance only, and any Prolam substitution should be verified against the complete selection chart or the Prolam online specifier. specifier.prolamnz.com. Alternatives may not be suitable for all situations.

hySPAN E = 13.2GPa	Prolam PL8 Alternative	Prolam PL12 Alternative
150 x 45	190 x 42 or 140 x 88	140 x 63
170 x 45	240 x 42 or 190 x 63	190 x 42
200 x 45	240 x 42 or 190 x 88	190 x 63
240 x 45	290 x 42 or 240 x 88	240 x 63
300 x 45	315 x 63 or 290 x 88	290 x 63
360 x 45	360 x 88	360 x 63
400 x 45	405 x 88	405 x 63
150 x 63	190 x 63	140 x 88
170 x 63	190 x 88 or 240 x 42	190 x 63
200 x 63	240 x 63	190 x 88
240 x 63	290 x 63	240 x 88
300 x 63	315 x 88 or 360 x 63	290 x 88
360 x 63	405 x 88 or 450 x 63	360 x 88
400 x 63	450 x 88	405 x 88
600 x 63	N/A	595 x 88
150 x 90	190 x 88	190 x 63
170 x 90	240 x 63	240 x 42
200 x 90	240 x 88	240 x 63
240 x 90	315 x 88	290 x 63
300 x 90	360 x 88	315 x 88
360 x 90	450 x 88	405 x 88
400 x 90	495 x 88	450 x 88

This table applies only to Prolam products.

Alternative to Flitch Beam

Prolam® sizes are based on equivalent defection. These tables are for guidance only, and any Prolam substitution should be verified against the complete selection chart or the Prolam online specifier. specifier.prolamnz.com. Alternatives may not be suitable for all situations.

Flitch Beam	Prolam PL8 Alternative	Prolam PL12 Alternative	Prolam PLX20 Alternative
FB15L	190 x 63	140 x 90 or 190 x 42	-
FB20M	290 x 90	240 x 90	240 x 90
FB25L	290 x 90	290 x 63	240 x 90
FB25M	360 x 90 or 315 x 112	315 x 90 or 290 x 112	290 x 90
FB30M	405 x 90	360 x 90	290 x 90*

*PLX20-290x90 is the closest equavilent to FB30M.

Alternative to Round Poles

Prolam alternatives are intended for small end diameter (SED) round construction poles conforming to the requirements of NZS 3605 for the normal category with a minimum outer zone density of 350 kg/m3.

Pole Height (m)	150ø	175ø	200ø	225ø	250ø
2.4	PL8-180	PL8-220 or PL12-180	PL8-220	PL8-260	PL8-300 or PL12-260
3	PL8-180	PL8-220 or PL12-180	PL8-260 or PL12-220	PL8-260	PL8-300 or PL12-260
3.6	PL8-180	PL8-220	PL8-260 or PL12-220	PL8-260	PL8-300 or PL12-260
4.2	PL8-180	PL8-220	PL8-260 or PL12-220	PL8-260	PL8-300 or PL12-260
4.8	PL8-220 or PL12-180	PL8-220	PL8-260 or PL12-220	PL8-260	PL8-300 or PL12-260
5.4	PL8-220 or PL12-180	PL8-220	PL8-260 or PL12-220	PL8-300 or PL12-260	PL8-300
6	PL8-220 or PL12-180	PL8-220	PL8-260 or PL12-220	PL8-300 or PL12-260	PL8-300

This table applies only to Prolam products.

Alternative to LVL11

Prolam® sizes are based on equivalent defection. These tables are for guidance only, and any Prolam substitution should be verified against the complete selection chart or the Prolam online specifier. specifier.prolamnz.com. Alternatives may not be suitable for all situations.

LVL11 E = 11GPa	Prolam PL8 Alternative	Prolam PL12 Alternative
140 x 45	190 x 42 or 140 x 63	140 x 42
190 x 45	190 x 63 or 240 x 42	190 x 42
200 x 45	240 x 42 or 190 x 88	190 x 63 or 240 x 42
240 x 45	290 x 42 or 240 x 63	240 x 42
300 x 45	315 x 63 or 290 x 88	315 x 42 or 290 x 63
360 x 45	360 x 63	360 x 42
400 x 45	405 x 63	405 x 42
140 x 63	190 x 42	140 x 63
190 x 63	190 x 88 or 240 x 63	190 x 63
200 x 63	240 x 63	190 x 88 or 240 x 42
240 x 63	290 x 63	240 x 63
300 x 63	315 x 88 or 360 x 63	290 x 88 or 315 x 63
360 x 63	360 x 88 or 405 x 63	315 x 88 or 360 x 63
400 x 63	405 x 88	405 x 63
140 x 90	190 x 63	140 x 88
190 x 90	240 x 63	190 x 88
200 x 90	240 x 88	240 x 63
240 x 90	315 x 63	240 x 88 or 290 x 63
300 x 90	360 x 88	315 x 88 or 360 x 63
360 x 90	405 x 88	360 x 88 or 405 x 63
400 x 90	450 x 88	405 x 88

This table applies only to Prolam products.

Alternative to GL13 (includes Hyne LGL)

Prolam® sizes are based on equivalent defection. These tables are for guidance only, and any Prolam substitution should be verified against the complete selection chart or the Prolam online specifier. specifier.prolamnz.com. Alternatives may not be suitable for all situations.

GL13 E = 13.3GPa	Prolam PL8 Alternative	Prolam PL12 Alternative
140 x 42	190 x 42 or 140 x 88	140 x 63 or 190 x 42
190 x 42	240 x 42 or 190 x 88	190 x 63 or 240 x 42
240 x 42	290 x 42 or 240 x 88	240 x 63 or 290 x 42
290 x 42	315 x 63 or 290 x 88	290 x 63 or 315 x 42
315 x 42	360 x 63 or 290 x 88	290 x 63 or 360 x 42
360 x 42	360 x 88	360 x 63 or 405 x 42
405 x 42	405 x 88	405 x 63
140 x 63	190 x 42	140 x 88 or 190 x 42
190 x 63	240 x 63	190 x 88 or 240 x 63
240 x 63	290 x 63	240 x 88 or 290 x 42
290 x 63	315 x 88	290 x 88 or 315 x 63
315 x 63	360 x 88	315 x 88 or 360 x 63
360 x 63	405 x 88 or 450 x 63	360 x 88 or 405 x 63
405 x 63	450 x 88	405 x 88 or 450 x 63
140 x 90	190 x 63	190 x 42
190 x 90	240 x 88	240 x 63
240 x 90	290 x 88	290 x 63
290 x 90	360 x 88	315 x 88
315 x 90	405 x 88	360 x 88
360 x 90	450 x 88	405 x 88
405 x 90	495 x 88	450 x 88

This table applies only to Prolam products.

Alternative to Hyne15

Prolam® sizes are based on equivalent defection. These tables are for guidance only, and any Prolam substitution should be verified against the complete selection chart or the Prolam online specifier. specifier.prolamnz.com. Alternatives may not be suitable for all situations.

Hyne15 E 14.8GPa	Prolam PL8 Alternative	Prolam PL12 Alternative	Prolam PLX20
130 x 65	190 x 63	140 x 90	-
165 x 65	190 x 90	190 x 63	-
195 x 65	240 x 63	190 x 90	-
230 x 65	290 x 63	240 x 90	-
260 x 65	290 x90	290 x 63	240 x 90
295 x 65	360 x 90	290 x 90	240 x 90
330 x 65	405 x 90	360 x 63	290 x 90
360 x 65	450 x 63 or 405 x 90	405 x 63 or 360 x 90	290 x 90
395 x 65	495 x 63 or 450 x 90	450 x 63 or 405 x 90	-
425 x 65	540 x 63 or 495 x 90	450 x 90	-
460 x 65	595 x 63 or 540 x 90	450 x 90	-
495 x 65	595 x 90	495 x 90	-
230 x 85	290 x 90	290 x 63	240 x 90
260 x 85	315 x 90	290 x 90	240 x 90
295 x 85	360 x 90	315 x 90	290 x 90
330 x 85	405 x 90	360 x 90	290 x 90
360 x 85	450 x 90	405 x 90	-
395 x 85	495 x 90	450 x 90	-
425 x 85	595 x 63 or 540 x 90	540 x 63 or 495 x 90	-
460 x 85	595 x 90	495 x 90	-
495 x 85	-	595 x 63 or 540 x 90	-
525 x 85	-	595 x 90	-

This table applies only to Prolam products.

Alternative to SG8

Prolam® sizes are based on equivalent defection. These tables are for guidance only, and any Prolam substitution should be verified against the complete selection chart or the Prolam online specifier. specifier.prolamnz.com. Alternatives may not be suitable for all situations.

SG8	Prolam PL8 Alternative	Prolam PL12 Alternative
140 x 45*	140 x 42	140 x 42 or 90 x 90
190 x 45*	190 x 42 or 140 x 90	190 x 42 or 140 x 63
240 x 45*	240 x 42 or 190 x 63	190 x 42
290 x 45*	290 x 42 or 240 x 63	240 x 42 or 190 x 90
140 x 70**	140 x 63	140 x 42
190 x 70**	190 x 63	190 x 42
240 x 70**	240 x 63	240 x 42
290 x 70**	290 x 63	290 x 42
140 x 90**	190 x 42 or 140 x 90	140 x 63
190 x 90**	240 x 42 or 190 x 93	190 x 63
240 x 90**	240 x 90	240 x 63
290 x 90**	290 x 90	290 x 63

*One Member E_{lb} = 5.4 GPa

**Two Members E = 6.7 GPa

This table applies only to Prolam products.

Comparison with hyJOISTS
Domestic Floors

1.5kPa Live load SINGLE SPAN

Prolam® sizes are based on equivalent defection. These tables are for guidance only, and any Prolam substitution should be verified against the complete selection chart or the Prolam online specifier. specifier.prolamnz.com. Alternatives may not be suitable for all situations.

hyJOIST	Joist Spacing	Span Range	Prolam Equivalent			
			Joist size	Spacing	Grade	Max Span
HJ200 45	450	3.5 to 3.8	190x63	450	PL8	3.6
			240x42	450	PL8	4.1
			190x42	450	PL12	3.5
HJ200 45	600	3.1 to 3.6	190x63	600	PL8	3.6
			240x42	600	PL8	4.0
			190x42	600	PL12	3.5
HJ240 63	450	4.4 to 4.9	240x63	450	PL8	4.7
			290x42	450	PL8	4.9
			240x42	450	PL12	4.6
HJ240 63	600	4.0 to 4.5	240x63	600	PL8	4.6
			290x42	600	PL8	4.8
			240x42	600	PL12	4.5
HJ240 90	450	4.9 to 5.4	290x63	450	PL8	5.7
			315x42	450	PL8	5.4
			240x63	450	PL12	5.3
			290x42	450	PL12	5.6
HJ240 90	600	4.5 to 5.0	290x63	600	PL8	5.6
			315x42	600	PL8	5.3
			240x63	600	PL12	5.2
			290x42	600	PL12	5.5

This table applies only to Prolam products.

Comparison with hyJOISTS - Continued
Domestic Floors

1.5kPa Live load SINGLE SPAN

Prolam® sizes are based on equivalent defection. These tables are for guidance only, and any Prolam substitution should be verified against the complete selection chart or the Prolam online specifier. specifier.prolamnz.com. Alternatives may not be suitable for all situations.

hyJOIST	Joist Spacing	Span Range	Prolam Equivalent			
			Joist size	Spacing	Grade	Max Span
HJ300 63	450	5.0 to 5.5	290x63	450	PL8	5.7
			315x42	450	PL8	5.4
			240x63	450	PL12	5.3
			290x42	450	PL12	5.6
HJ300 63	600	4.6 to 5.1	290x63	600	PL8	5.6
			315x42	600	PL8	5.3
			240x63	600	PL12	5.2
			290x42	600	PL12	5.5
HJ300 90	450	5.6 to 6.1	315x63	450	PL8	6.2
			360x42	450	PL8	6.2
			290x63	450	PL12	6.4
			315x42	400	PL12	6.1
HJ300 90	600	5.2 to 5.7	315x63	600	PL8	6.0
			360x42	600	PL8	5.9
			290x63	600	PL12	6.1
			315x42	600	PL12	5.9
HJ360 63	450	5.6 to 6.2	315x63	450	PL8	6.2
			360x42	450	PL8	6.2
			290x63	450	PL12	6.4
			315x42	450	PL12	6.1
HJ360 63	600	5.2 to 5.7	315x63	600	PL8	6.0
			360x42	600	PL8	5.9
			290x63	600	PL12	6.1
			315x42	600	PL12	5.9

This table applies only to Prolam products.

Comparison with hyJOISTS - Continued
Domestic Floors

1.5kPa Live load SINGLE SPAN

Prolam® sizes are based on equivalent defection. These tables are for guidance only, and any Prolam substitution should be verified against the complete selection chart or the Prolam online specifier. specifier.prolamnz.com. Alternatives may not be suitable for all situations.

hyJOIST	Joist Spacing	Span Range	Prolam Equivalent			
			Joist size	Spacing	Grade	Max Span
HJ360 90	450	6.3 to 6.8	360x63	450	PL8	7.1
			405x42	450	PL8	6.9
			315x63	450	PL12	7.0
			360x42	450	PL12	7.0
HJ360 90	600	5.8 to 6.3	360x63	600	PL8	6.6
			405x42	600	PL8	6.5
			315x63	600	PL12	6.5
			360x42	600	PL12	6.5
HJ400 90	450	6.8 to 7.2	405x63	450	PL8	7.8
			360x63	450	PL12	7.8
			405x42	450	PL12	7.7
HJ400 90	600	6.3 to 6.7	405x63	600	PL8	7.2
			360x63	600	PL12	7.2
			405x42	600	PL12	7.1

This table applies only to Prolam products.

Span Tables



Timber properties

Used in span table calculations

Dry Use

Characteristic Stresses and Elastic Moduli for Prolam (Glulam Grades)

	Characteristic Strengths (MPa)					Elastic Moduli (MPa)	
	PL Grade	Bending	Tension parallel to grain	Shear in Beam	Compression parallel to grain	Modulus of elasticity parallel to the grain	Modulus of rigidity for beams
Prolam	PL 12	25	12.5	3.7	29	11500	770
Prolam	PL 8	19	10	3.7	24	8000	530
Prolam	PLX20	40†/45‡	4	3.7	18	20000†/21000‡	480

† PLX20-250100
‡ PLX20-300100

Notes
(1) PLX20 intended for use as a beam and not as a tension or compression member.
(2) PLX20 bending strength and MoE about the major axis have been determined from testing. Other properties are based on SG6 timber.
(3) For compression perpendicular to the grain, use 8.9 MPa dry and 5.3 MPa wet as per NZS 3603 for Radiata Pine for all PL grades.
(4) Higher grades (i.e. PL12, or PLX20) will give greater span and load carrying capability than PL8 for the same section size.

Wet Use – (H5 & H3.2 treated)

Characteristic Stresses and Elastic Moduli for Prolam (Glulam Grades)

	Characteristic Strengths (MPa)				Elastic Moduli (MPa)	
PL Grade	Bending	Tension parallel to grain	Shear in Beam	Compression parallel to grain	Modulus of elasticity parallel to the grain	Modulus of rigidity for beams
PL 12	20	10	2.5	23.2	9200	610
PL 8	15.2	8.0	2.5	19.2	6400	420

Design Data

The tables herein have been designed according to the following loads:

Roof				
Dead Load		Live Load	Snow Load	Wind Load
Lighweight Roof	Ceiling	0.25 kPa Uniform	0.4kPa	High Wind (NZS3604:2011)
0.25 kPa	0.15 kPa	1.1 kN point load		

Floor			
Domestic Floor		Deck	
Dead Load	Live Load	Dead Load	Live Load
0.40 kPa	1.5 kPa Uniform	0.40 kPa	2 kPa Uniform
	1.80 kN Point Load		1.80 kN Point Load

Deflection Limits	
Lintel	Span / 300 or 12mm
Rafter	Span / 300 or 25mm
Bearer	Span / 300 or 12mm
Joist	Span / 350 or 20mm

Notes
1. 750mm eaves width has been included in the derivation of the tables.
2. Spans are horizontal measurements. For heavy roofs or over 25° pitch roofs, use the Prolam® Specifier.
3. The span tables in this booklet do not apply to the bandsawn product. Use the Prolam® Specifier.

November 2022

PRODUCER STATEMENT

TASMAN CONSULTING ENGINEERS CIVIL & STRUCTURAL


Tasman Consulting Engineers Ltd have been engaged by Prowood to prepare span tables and charts for the Prolam® lintels, beams and posts as presented in the Prolam® Post and Beam Manual.

The design has been carried out using sound and widely accepted engineering principles to the requirements of AS/NZS1170:2002, NZS3603:1993 and NZS3604:2011 using the timber properties for PL8 and PL12 glue laminated timber.

Tasman Consulting Engineers Limited
195 Queen St, PO Box 3631
Richmond, NELSON 7050

OLIVER GREEFF
BE(Civil) CMEngNZ (No.1158805) CPEng IntPE

Span Tables



A ≤ ¼ (A + B), R = B + 2A

Table 1

Prolam® Lintel supporting roof and ceiling

		Roof Span (m) 'R'	2.0	3.0	4.0	5.0	6.0	7.0	8.0	9.0	10.0	11.0	12.0
		Lintel Size	Maximum Lintel Span (m)										
PL8	Light Roof	**PL8H1-150100** 140 x 90mm	2.9	2.7	2.6	2.5	2.4	2.3	2.2	2.1	2.0	1.9	1.9
		PL8H1-200100 190 x 90mm	3.7	3.4	3.3	3.1	3.0	2.9	2.8	2.8	2.7	2.6	2.5
		PL8H1-250100 240 x 90mm	4.4	4.1	3.9	3.7	3.6	3.5	3.4	3.3	3.2	3.2	3.1
		PL8H1-300100 290 x 90mm	5.1	4.8	4.5	4.3	4.2	4.0	3.9	3.8	3.7	3.7	3.6
		PL8H1-350100 315 x 90mm	5.4	5.1	4.8	4.6	4.4	4.3	4.2	4.1	4.0	3.9	3.8
		PL8H1-400100 360 x 90mm	6.0	5.6	5.3	5.1	4.9	4.8	4.6	4.5	4.4	4.2	4.1
PL12	Light Roof	**PL12H1-150100** 140 x 90mm	3.2	3.0	2.8	2.7	2.6	2.5	2.5	2.4	2.3	2.2	2.1
		PL12H1-200100 190 x 90mm	4.0	3.8	3.6	3.4	3.3	3.2	3.1	3.0	3.0	2.9	2.9
		PL12H1-250100 240 x 90mm	4.8	4.5	4.3	4.1	4.0	3.8	3.7	3.6	3.6	3.5	3.4
		PL12H1-300100 290 x 90mm	5.6	5.2	5.0	4.7	4.6	4.4	4.3	4.2	4.1	4.0	3.9
		PL12H1-350100 315 x 90mm	5.9	5.5	5.3	5.1	4.9	4.7	4.6	4.5	4.4	4.3	4.2
		PL12H1-400100 360 x 90mm	6.5	6.1	5.8	5.6	5.4	5.2	5.1	5.0	4.8	4.7	4.6

Note The design parameters are specified in the design data page.
For different parameters, refer to Prolam Online Specifier at specifier.prolamnz.com

This table applies only to Prolam products.

Span Tables




Table 2

Prolam® Ridge Beam supporting roof and ceiling. (Rafters at 1200mm CRS MAX)

	Roof Span (m) 'R'	2.0	3.0	4.0	5.0	6.0	7.0	8.0	9.0	10.0	11.0	12.0
	Ridge Beam Size	**Maximum Ridge Beam Span (m)**										
PL8	**PL8H1-150100** 140 x 90mm	3.2	3.0	2.8	2.7	2.5	2.4	2.4	2.3	2.2	2.1	2.0
	PL8H1-200100 190 x 90mm	4.2	3.8	3.5	3.4	3.2	3.1	3.0	2.9	2.8	2.7	2.7
	PL8H1-250100 240 x 90mm	5.0	4.6	4.2	4.0	3.8	3.7	3.6	3.4	3.4	3.3	3.2
	PL8H1-300100 290 x 90mm	5.8	5.3	4.9	4.6	4.4	4.2	4.1	4.0	3.9	3.8	3.7
	PL8H1-35000 315 x 90mm	6.2	5.6	5.2	4.9	4.7	4.5	4.4	4.2	4.1	4.0	3.9
	PL8H1-400100 360 x 90mm	6.8	6.2	5.8	5.5	5.2	5.0	4.8	4.7	4.6	4.5	4.3
PL12	**PL12H1-150100** 140 x 90mm	3.6	3.3	3.1	2.9	2.8	2.7	2.6	2.5	2.4	2.4	2.3
	PL12H1-200100 190 x 90mm	4.6	4.2	3.9	3.7	3.5	3.4	3.3	3.2	3.1	3.0	2.9
	PL12H1-250100 240 x 90mm	5.5	5.0	4.6	4.4	4.2	4.0	3.9	3.8	3.7	3.6	3.5
	PL12H1-300100 290 x 90mm	6.4	5.8	5.4	5.1	4.8	4.7	4.5	4.4	4.3	4.2	4.1
	PL12H1-350100 315 x 90mm	6.7	6.1	5.7	5.4	5.2	5.0	4.8	4.7	4.5	4.4	4.3
	PL12H1-400100 360 x 90mm	7.4	6.8	6.3	6.0	5.7	5.5	5.3	5.2	5.0	4.9	4.8

Note The design parameters are specified in the design data page.
For different parameters, refer to Prolam Online Specifier at specifier.prolamnz.com

This table applies only to Prolam products.

Span Tables




Table 3

Prolam® Rafter for internal use supporting roof and ceiling

Rafter Spacing (m)	0.6	0.75	0.9	1.0	1.2
Rafter Size	**Maximum Rafter Span (m)**				
PLVL8H3-15075 140 x 63mm	3.3	3.0	2.9	2.8	2.6
	B	B	B	B	B
PLVL8H3-20075 190 x 63mm	4.4	4.1	3.9	3.8	3.6
	B	B	B	B	B
PLVL8H3-25075 240 x 63mm	5.4	5.1	4.9	4.7	4.5
	B	B	B	B	B
PLVL8H3-30075 290 x 63mm	6.5	6.1	5.8	5.7	5.4
	B	B	B	B	B
PLVL8H3-35075 315 x 63mm	6.9	6.6	6.3	6.1	5.8
	B	B	B	B	B
PLVL8H3-40075 360 x 63mm	7.5	7.3	7.0	6.9	6.6
	B	B	B	B	C

Rafter Spacing (m)	0.6	0.75	0.9	1.0	1.2
Rafter Size	**Maximum Rafter Span (m)**				
PLVL8H3-15050 140 x 42mm	2.6	2.5	2.4	2.4	2.3
	B	B	B	B	B
PLVL8H3-20050 190 x 42mm	3.9	3.6	3.5	3.3	3.2
	B	B	B	B	B
PLVL8H3-25050 240 x 42mm	4.9	4.6	4.3	4.2	4.0
	B	B	B	B	B
PLVL8H3-30050 290 x 42mm	5.8	5.5	5.2	5.1	4.8
	B	B	B	B	B
PLVL8H3-35050 315 x 42mm	6.3	5.9	5.6	5.5	5.2
	B	B	B	B	B
PLVL8H3-40050 360 x 42mm	7.0	6.7	6.4	6.2	5.9
	B	B	B	B	C

Fixing type

B 2/100 x 3.75 skewed nails and 1 wire dog or 2.7kN connection

C 2/100 x 3.75 skewed nails and 2 wire dog or 4.7kN connection

End fixing to resist uplift – refer also to NZS3604: 2011

Note The design parameters are specified in the design data page.
For different parameters, refer to Prolam Online Specifier at specifier.prolamnz.com


This table applies only to Prolam products.

Span Tables

Table 4

Prolam® Veranda Rafter (wet use) supporting roof without ceiling

Rafter Spacing (m)	0.6	0.75	0.9	1.0	1.2
Rafter Size	**Maximum Rafter Span (m)**				
PLVL8H3-10050 88 x 42mm	1.0	1.0	1.0	0.9	0.9
	B	B	B	B	B
PLVL8H3-15050 140 x 42mm	2.3	2.2	2.2	2.2	2.1
	B	B	B	B	B
PLVL8H3-20050 190 x 42mm	3.7	3.5	3.4	3.4	3.2
	B	B	B	B	B
PLVL8H3-25050 240 x 42mm	4.9	4.7	4.6	4.5	4.2
	B	B	B	B	B
PLVL8H3-30050 290 x 42mm	6.1	5.8	5.5	5.3	5.1
	B	B	B	B	C
PLVL8H3-35050 315 x 42mm	6.6	6.2	5.9	5.8	5.5
	B	B	B	C	C
PLVL8H3-40050 360 x 42mm	7.2	6.9	6.6	6.4	6.1
	B	B	C	C	C



Fixing type

B 2/100 x 3.75 skewed nails and 1 wire dog or 2.7kN connection

C 2/100 x 3.75 skewed nails and 2 wire dog or 4.7kN connection

End fixing to resist uplift - Refer also to NZS3604:2011

Rafter Spacing (m)	0.6	0.75	0.9	1.0	1.2
Rafter Size	**Maximum Rafter Span (m)**				
PLVL8H3-10075 88 x 63mm	1.5	1.4	1.4	1.4	1.4
	B	B	B	B	B
PLVL8H3-15075 140 x 63mm	3.3	3.2	3.1	3.0	2.8
	B	B	B	B	B
PLVL8H3-20075 190 x 63mm	4.5	4.3	4.1	4.0	3.8
	B	B	B	B	B
PLVL8H3-25075 240 x 63mm	5.6	5.3	5.1	5.0	4.7
	B	B	B	B	B
PLVL8H3-30075 290 x 63mm	6.6	6.3	6.1	5.9	5.7
	B	B	B	B	C
PLVL8H3-35075 315 x 63mm	7.0	6.8	6.6	6.4	6.1
	B	B	B	C	C
PLVL8H3-40075 360 x 63mm	7.7	7.4	7.2	7.1	6.8
	B	B	C	C	C

Rafter Spacing (m)	0.6	0.75	0.9	1.0	1.2
Rafter Size	**Maximum Rafter Span (m)**				
PLVL8H3-100100 88 x 88mm	2.0	1.9	1.9	1.9	1.8
	B	B	B	B	B
PLVL8H3-150100 140 x 88mm	3.7	3.5	3.4	3.3	3.1
	B	B	B	B	B
PLVL8H3-200100 190 x 88mm	4.9	4.7	4.5	4.4	4.2
	B	B	B	B	B
PLVL8H3-250100 240 x 88mm	6.0	5.8	5.5	5.4	5.2
	B	B	B	B	C
PLVL8H3-300100 290 x 88mm	7.0	6.8	6.5	6.4	6.1
	B	B	B	C	C
PLVL8H3-350100 315 x 88mm	7.3	7.1	6.9	6.8	6.6
	B	B	B	C	C
PLVL8H3-400100 360 x 88mm	8.0	7.8	7.6	7.5	7.3
	B	B	C	C	C

Note The design parameters are specified in the design data page.
For different parameters, refer to Prolam Online Specifier at specifier.prolamnz.com


This table applies only to Prolam products.

Span Tables

Table 5

Prolam® Veranda Rafter (wet use) supporting roof and ceiling

Rafter Spacing (m)	0.6	0.75	0.9	1.0	1.2
Rafter Size	**Maximum Rafter Span (m)**				
PLVL8H3-10050 88 x 42mm	0.9	0.9	0.9	0.8	0.8
	B	B	B	B	B
PLVL8H3-15050 140 x 42mm	2.1	2.0	2.0	1.9	1.9
	B	B	B	B	B
PLVL8H3-20050 190 x 42mm	3.3	3.2	3.1	3.0	2.8
	B	B	B	B	B
PLVL8H3-25050 240 x 42mm	4.5	4.2	4.0	3.8	3.6
	B	B	B	B	B
PLVL8H3-30050 290 x 42mm	5.4	5.0	4.8	4.6	4.4
	B	B	B	B	B
PLVL8H3-35050 315 x 42mm	5.8	5.5	5.2	5.0	4.8
	B	B	B	B	B
PLVL8H3-40050 360 x 42mm	6.6	6.2	5.9	5.7	5.4
	B	B	B	B	B



Fixing type

B 2/100 x 3.75 skewed nails and 1 wire dog or 2.7kN connection

C 2/100 x 3.75 skewed nails and 2 wire dogs or 4.7kN connection

End fixing to resist uplift -Refer also to NZS3604: 2011

Rafter Spacing (m)	0.6	0.75	0.9	1.0	1.2
Rafter Size	**Maximum Rafter Span (m)**				
PLVL8H3-10075 88 x 63mm	1.4	1.4	1.3	1.3	1.3
	B	B	B	B	B
PLVL8H3-15075 140 x 63mm	3.0	2.8	2.7	2.6	2.4
	B	B	B	B	B
PLVL8H3-20075 190 x 63mm	4.0	3.8	3.6	3.5	3.3
	B	B	B	B	B
PLVL8H3-25075 240 x 63mm	5.0	4.7	4.5	4.4	4.2
	B	B	B	B	B
PLVL8H3-30075 290 x 63mm	6.0	5.7	5.4	5.3	5.0
	B	B	B	B	B
PLVL8H3-35075 315 x 63mm	6.5	6.1	5.8	5.7	5.4
	B	B	B	B	B
PLVL8H3-40075 360 x 63mm	7.1	6.9	6.6	6.4	6.1
	B	B	B	B	C

Rafter Spacing (m)	0.6	0.75	0.9	1.0	1.2
Rafter Size	**Maximum Rafter Span (m)**				
PLVL8H3-100100 88 x 88mm	1.9	1.8	1.8	1.7	1.7
	B	B	B	B	B
PLVL8H3-150100 140 x 88mm	3.3	3.1	2.9	2.9	2.7
	B	B	B	B	B
PLVL8H3-200100 190 x 88mm	4.4	4.2	4.0	3.8	3.7
	B	B	B	B	B
PLVL8H3-250100 240 x 88mm	5.4	5.2	4.9	4.8	4.6
	B	B	B	B	B
PLVL8H3-300100 290 x 88mm	6.5	6.1	5.9	5.7	5.5
	B	B	B	B	B
PLVL8H3-350100 315 x 88mm	6.9	6.6	6.4	6.2	5.9
	B	B	B	B	B
PLVL8H3-400100 360 x 88mm	7.5	7.3	7.0	6.9	6.7
	B	B	B	B	C


Note The design parameters are specified in the design data page.
For different parameters, refer to Prolam Online Specifier at specifier.prolamnz.com

This table applies only to Prolam products.

Span Tables

Table 6

Prolam® Veranda Lintel (wet use) supporting roof with and without ceiling



		Roof Width (m) 'R'	1.2	1.8	2.4	3.0	3.6	4.2	4.8	5.4	6.0	6.6
		Lintel Size	Maximum lintel span (m)									
PL8	No Ceiling	PLVL8H3-15075 140 x 63mm	2.7	2.5	2.4	2.3	2.3	2.2	2.1	2.1	2.0	2.0
		PLVL8H3-20075 190 x 63mm	3.4	3.2	3.1	3.0	2.9	2.8	2.7	2.7	2.6	2.5
		PLVL8H3-25075 240 x 63mm	4.0	3.8	3.7	3.5	3.4	3.3	3.3	3.2	3.1	3.1
		PLVL8H3-30075 290 x 63mm	4.7	4.4	4.2	4.1	4.0	3.9	3.8	3.7	3.6	3.5
		PLVL8H3-35075 315 x 63mm	5.0	4.7	4.5	4.4	4.2	4.1	4.0	3.9	3.8	3.8
		PLVL8H3-40075 360 x 63mm	5.5	5.2	5.0	4.8	4.7	4.5	4.4	4.3	4.2	4.2
		PLVL8H3-150100 140 x 88mm	2.9	2.8	2.7	2.6	2.5	2.4	2.3	2.3	2.2	2.2
		PLVL8H3-200100 190 x 88mm	3.7	3.5	3.4	3.2	3.1	3.0	3.0	2.9	2.8	2.8
		PLVL8H3-250100 240 x 88mm	4.4	4.2	4.0	3.9	3.7	3.6	3.5	3.5	3.4	3.3
		PLVL8H3-300100 290 x 88mm	5.1	4.8	4.6	4.5	4.3	4.2	4.1	4.0	3.9	3.8
		PLVL8H3-350100 315 x 88mm	5.4	5.1	4.9	4.8	4.6	4.5	4.4	4.3	4.2	4.1
		PLVL8H3-400100 360 x 88mm	6.0	5.7	5.5	5.3	5.1	5.0	4.8	4.7	4.6	4.5
	With Ceiling	PLVL8H3-15075 140 x 63mm	2.5	2.4	2.2	2.1	2.1	2.0	1.9	1.9	1.8	1.8
		PLVL8H3-20075 190 x 63mm	3.4	3.2	3.0	2.9	2.8	2.7	2.6	2.5	2.5	2.4
		PLVL8H3-25075 240 x 63mm	4.0	3.8	3.7	3.6	3.4	3.3	3.3	3.2	3.1	3.0
		PLVL8H3-30075 290 x 63mm	4.7	4.4	4.3	4.1	4.0	3.9	3.8	3.7	3.6	3.5
		PLVL8H3-35075 315 x 63mm	5.0	4.7	4.5	4.4	4.2	4.1	4.0	3.9	3.8	3.8
		PLVL8H3-40075 360 x 63mm	5.5	5.2	5.0	4.8	4.7	4.6	4.4	4.3	4.2	4.2
		PLVL8H3-150100 140 x 88mm	2.8	2.6	2.5	2.4	2.3	2.2	2.1	2.1	2.0	2.0
		PLVL8H3-200100 190 x 88mm	3.7	3.5	3.3	3.2	3.1	3.0	2.9	2.8	2.7	2.7
		PLVL8H3-250100 240 x 88mm	4.4	4.2	4.0	3.9	3.7	3.6	3.5	3.5	3.4	3.3
		PLVL8H3-300100 290 x 88mm	5.1	4.8	4.6	4.5	4.3	4.2	4.1	4.0	3.9	3.8
		PLVL8H3-350100 315 x 88mm	5.4	5.1	4.9	4.7	4.6	4.5	4.4	4.3	4.2	4.1
		PLVL8H3-400100 360 x 88mm	6.0	5.7	5.4	5.3	5.1	4.9	4.8	4.7	4.6	4.5


Note The design parameters are specified in the design data page.
For different parameters, refer to Prolam Online Specifier at specifier.prolamnz.com

This table applies only to Prolam products.

Span Tables

Table 7

Prolam® Floor Beam supporting joists



		Joist Span (m) 'F'	2.4	3.0	3.6	4.8	6.0	7.2	8.4
		Beam Size	Maximum Beam Span (m)						
PL8		PL8H1-150100 140 x 90mm	2.2	2.2	2.1	1.8	1.6	1.4	1.3
		PL8H1-200100 190 x 90mm	3.0	3.0	2.8	2.4	2.2	2.0	1.8
		PL8H1-250100 240 x 90mm	3.8	3.8	3.6	3.1	2.8	2.5	2.3
		PL8H1-300100 290 x 90mm	4.6	4.6	4.3	3.8	3.4	3.1	2.8
		PL8H1-350100 315 x 90mm	5.0	5.0	4.7	4.1	3.7	3.3	3.0
PL12		PL12H1-150100 140 x 90mm	2.5	2.5	2.4	2.1	1.8	1.7	1.5
		PL12H1-200100 190 x 90mm	3.4	3.4	3.3	2.8	2.5	2.3	2.1
		PL12H1-250100 240 x 90mm	4.3	4.3	4.1	3.6	3.2	2.9	2.6
		PL12H1-300100 290 x 90mm	5.2	5.2	5.0	4.3	3.9	3.5	3.2
		PL12H1-350100 315 x 90mm	5.6	5.6	5.4	4.7	4.2	3.8	3.5

Note For 1.5 kPa L.L. refer to Prolam Online at specifier.prolamnz.com

Note The design parameters are specified in the design data page.
For different parameters, refer to Prolam Online Specifier at specifier.prolamnz.com

This table applies only to Prolam products.


Span Tables

Table 8a

Prolam® Floor Joist PL8

Notes:

1. Timber grade PL8 – dry use.
2. Joists do not support roof loads.
3. Spans may be increased by 10% for joists continuous over 2 or more equal spans.
4. Blocking required in accordance with NZS3604:2011 Clause 7.1.2.



	Joist Spacing (m)		400	450	600
	Joist Size (m)		Floor Joists Single Span (m)		
PL8	PL8H3-15050	140 x 42mm	1.6	1.6	1.6
	PL8H3-20050	190 x 42mm	2.6	2.6	2.6
	PL8H3-25050	240 x 42mm	3.7	3.7	3.6
	PL8H3-30050	290 x 42mm	4.5	4.5	4.4
	PL8H3-35050	315 x 42mm	4.9	4.9	4.8
	PL8H3-40050	360 x 42mm	5.6	5.6	5.4
	PL8H3-45050	405 x 42mm	6.3	6.3	5.9
	PL8H3-15075	140 x 63mm	2.0	2.0	2.0
	PL8H3-20075	190 x 63mm	3.3	3.3	3.3
	PL8H3-25075	240 x 63mm	4.2	4.2	4.2
	PL8H3-30075	290 x 63mm	5.1	5.1	5.1
	PL8H3-35075	315 x 63mm	5.6	5.6	5.4
	PL8H3-40075	360 x 63mm	6.4	6.4	6.0
	PL8H3-45075	405 x 63mm	7.2	7.0	6.5

Note The design parameters are specified in the design data page.
For different parameters, refer to Prolam Online Specifier at specifier.prolamnz.com

These span tables apply only to Prolam products.


Span Tables

Table 8b

Prolam® Floor Joist PL12

Notes:

1. Timber grade PL12 – dry use.
2. Joists do not support roof loads.
3. Spans may be increased by 10% for joists continuous over 2 or more equal spans.
4. Blocking required in accordance with NZS3604:2011 Clause 7.1.2.



	Joist Spacing (m)		400	450	600
	Joist Size (m)		Floor Joists Single Span (m)		
PL12	PL12H3-15050	140 x 42mm	2.0	2.0	2.0
	PL12H3-20050	190 x 42mm	3.2	3.2	3.2
	PL12H3-25050	240 x 42mm	4.2	4.2	4.1
	PL12H3-30050	290 x 42mm	5.1	5.1	5.0
	PL12H3-35050	315 x 42mm	5.5	5.5	5.3
	PL12H3-40050	360 x 42mm	6.3	6.3	5.9
	PL12H3-45050	405 x 42mm	7.1	7.0	6.5
	PL12H3-15075	140 x 63mm	2.4	2.4	2.4
	PL12H3-20075	190 x 63mm	3.8	3.8	3.7
	PL12H3-25075	240 x 63mm	4.8	4.8	4.7
	PL12H3-30075	290 x 63mm	5.8	5.8	5.6
	PL12H3-45075	315 x 63mm	6.3	6.3	5.9
	PL12H3-40075	360 x 63mm	7.2	7.1	6.6
	PL12H3-45075	405 x 63mm	8.0	7.7	7.2

Note The design parameters are specified in the design data page.
For different parameters, refer to Prolam Online Specifier at specifier.prolamnz.com

These span tables apply only to Prolam products.

Span Tables




Table 9

Prolam® Deck Bearer supporting deck and cantilever

Notes:

1. Minimum H3.2 treated – wet use.
2. Bearers do not support roof loads.
3. Maximum ballustrade weight 30kg/m.
4. Maximum joist cantilever 400mm.
5. Spans may be increased by 10% for bearers continuous over 2 or more spans.

	Joist Span (m)		0.9	1.2	1.5	1.8	2.4	3.0	3.6	4.2	4.8
	Bearer Size (m)		Maximum Bearer Span (m)								
PL8	**PL8H3-150100**	140 x 90mm	1.9	1.8	1.8	1.6	1.4	1.2	1.1	1.0	1.0
PL8	**PL8H3-200100**	190 x 90mm	2.6	2.5	2.4	2.2	1.9	1.7	1.6	1.4	1.3
PL8	**PL8H3-250100**	240 x 90mm	3.3	3.2	3.1	2.8	2.4	2.2	2.0	1.8	1.7
PL8	**PL8H3-300100**	290 x 90mm	4.0	3.9	3.7	3.4	3.0	2.6	2.4	2.2	2.1
PL8	**PL8H3-350100**	315 x 90mm	4.3	4.2	4.1	3.7	3.2	2.9	2.6	2.4	2.3
PL8	**PL8H3-400100**	360 x 90mm	4.9	4.8	4.6	4.3	3.7	3.3	3.0	2.8	2.6
PL12	**PL12H3-150100**	140 x 90mm	2.2	2.1	2.0	1.9	1.6	1.4	1.3	1.2	1.1
PL12	**PL12H3-200100**	190 x 90mm	3.0	2.9	2.8	2.6	2.2	2.0	1.8	1.7	1.5
PL12	**PL12H3-250100**	240 x 90mm	3.7	3.6	3.5	3.3	2.8	2.5	2.3	2.1	2.0
PL12	**PL12H3-300100**	290 x 90mm	4.5	4.4	4.2	3.9	3.4	3.0	2.8	2.6	2.4
PL12	**PL12H3-350100**	315 x 90mm	4.9	4.7	4.6	4.3	3.7	3.3	3.0	2.8	2.6
PL12	**PL12H3-400100**	360 x 90mm	5.6	5.4	5.2	4.9	4.2	3.8	3.5	3.2	3.0


Note The design parameters are specified in the design data page.
For different parameters, refer to Prolam Online Specifier at specifier.prolamnz.com

These span tables apply only to Prolam products.

Span Tables

Table 10

Prolam® Deck Joist



Notes:

1. Minimum H3.2 treated – wet use.
2. No ceiling or sofit lining.
3. Joists do not support roof loads.
4. Spans may be increased by 10% for joists continuous over 2 or more spans.
5. Blocking required in accordance with NZS3604:2011 Clause 7.1.2.

	Joist Spacing (m)		0.40	0.45	0.60
	Joist Size (m)		Deck Joists Single Span (m)		
PL8	**PL8H3-15050**	140 x 42mm	1.5	1.5	1.5
PL8	**PL8H3-20050**	190 x 42mm	2.4	2.4	2.4
PL8	**PL8H3-25050**	240 x 42mm	3.4	3.4	3.2
PL8	**PL8H3-30050**	290 x 42mm	4.2	4.2	3.8
PL8	**PL8H3-35050**	315 x 42mm	4.5	4.5	4.2
PL8	**PL8H3-40050**	360 x 42mm	5.2	5.2	4.8
PL8	**PL8H3-45050**	405 x 42mm	5.8	5.7	5.3
PL8	**PL8H3-15075**	140 x 63mm	1.8	1.8	1.8
PL8	**PL8H3-20075**	190 x 63mm	2.9	2.9	2.9
PL8	**PL8H3-25075**	240 x 63mm	3.9	3.9	3.6
PL8	**PL8H3-30075**	290 x 63mm	4.8	4.8	4.4
PL8	**PL8H3-35075**	315 x 63mm	5.2	5.2	4.8
PL8	**PL8H3-40075**	360 x 63mm	5.9	5.8	5.4
PL8	**PL8H3-45075**	405 x 63mm	6.5	6.3	5.9

Note The design parameters are specified in the design data page.
For different parameters, refer to Prolam Online Specifier at specifier.prolamnz.com


These span tables apply only to Prolam products.

Span Tables

Table 11

Prolam® Deck Post Bracing Units

1. Piles supporting timber deck constructed to NZS 3604:2011 Clause 7.4.
2. Post to bearer fixing is for lateral loads. Vertical (bearing) loads may require additional capacity
3. Footing depth is into Good Ground as defined by NZS3604



Note The design parameters are specified in the design data page. For different parameters, refer to Prolam Online Specifier at specifier.prolamnz.com

These span tables apply only to Prolam products.


Prolam Post Deck Pile	Height (m)	BU Rating	Footing Depth (m)	Footing Diameter (mm)	Post to bearer Fixing
PLPH5-150 135x135	0.75	20	1.0	450	6kN
	1.00	17	1.0	450	6kN
	1.20	15	1.0	450	6kN
	1.50	13	1.0	450	6kN
	1.80	12	1.0	450	6kN
PLPH5-200 180x180	1.00	40	1.2	450	6kN
	1.20	36	1.2	450	6kN
	1.50	31	1.2	450	6kN
	1.80	28	1.2	450	6kN
	2.10	25	1.2	450	6kN
	2.40	21	1.2	450	6kN
	2.70	15	1.2	450	6kN
	3.00	11	1.2	450	6kN
PLPH5-250 220x220	1.60	50	1.5	600	12kN
	1.80	47	1.5	600	12kN
	2.10	42	1.5	600	12kN
	2.40	39	1.5	600	12kN
	2.70	34	1.5	600	12kN
	3.00	25	1.5	600	12kN
	3.30	19	1.5	600	12kN
	3.60	15	1.5	600	12kN
PLPH5-300 260x260	2.20	67	1.7	600	12kN
	2.40	63	1.7	600	12kN
	2.70	58	1.7	600	12kN
	3.00	49	1.7	600	12kN
	3.30	37	1.7	600	12kN
	3.60	29	1.7	600	12kN
	3.90	23	1.7	600	12kN
	4.20	18	1.7	600	12kN
PLP12H5-150 135x135	0.75	26	1.1	450	6kN
	1.00	22	1.1	450	6kN
	1.20	20	1.1	450	6kN
	1.50	18	1.1	450	6kN
	1.80	15	1.1	450	6kN
	2.10	13	1.1	450	6kN
PLP12H5-200 180x180	1.00	53	1.3	450	6kN
	1.20	47	1.3	450	6kN
	1.50	41	1.3	450	6kN
	1.80	37	1.3	450	6kN
	2.10	33	1.3	450	6kN
	2.40	30	1.3	450	6kN
	2.70	22	1.3	450	6kN
	3.00	16	1.3	450	6kN
	3.30	12	1.3	450	6kN
PLP12H5-250 220x220	1.80	61	1.6	600	12kN
	2.10	55	1.6	600	12kN
	2.40	51	1.6	600	12kN
	2.70	47	1.6	600	12kN
	3.00	36	1.6	600	12kN
	3.30	27	1.6	600	12kN
	3.60	21	1.6	600	12kN
PLP12H5-300 260x260	2.20	88	1.8	600	12kN
	2.40	83	1.8	600	12kN
	2.70	77	1.8	600	12kN
	3.00	71	1.8	600	12kN
	3.30	53	1.8	600	12kN
	3.60	41	1.8	600	12kN
	3.90	33	1.8	600	12kN
	4.20	26	1.8	600	12kN

Prolam® Veranda/Carport Bracing Post

1. Earthquake zone 3 - Soil Class E
2. Post to bearer fixing is for lateral loads. Vertical bearing loads may require additional capacity.
3. Footing depth is into Good Ground. Footing is sized for resisting bracing loads only.
4. Requirements for resisting uplift will need to be calculated separately - Section 9 in NZS3604:2011 gives tables for the uplift force and volume of concrete required for posts.

Post selection steps:

1. Calculate total plan and face areas of the Veranda roof:
   Total Plan area: TPA = W x L
   Total Face area: TFA = H x L
2. Select the post size desired and the post height
3. Read off the maximum areas AP and AF for that post
4. Number of posts required will equal the maximum of: TPA/AP or TFA/AF
5. If the number of posts is more than desired then select a larger post size and repeat the calculations.



Example (PL8 Bracing Post Supporting Free Standing Veranda/Carport - Table 12a):

Roof Length = 6 Roof Width = 4 Roof Height = 1.2

TPA =24

TFA =7.2

Post size = 180x180 Post height = 2.1

AP =6.3 AF =2.6

TPA/AP =3.8 TFA/AF =2.8

Number of posts required = 4 (3.8 rounded up)

These span tables apply only to Prolam products.

Span Tables




Table 12a

Prolam® Bracing Post Veranda/Carport - free standing supporting roof and ceiling PL8

Post Size	Post Height (m)	Maximum plan area per post (AP) (m^2)	Maximum face area per post (AF) (m^2)	Footing Depth (m)	Footing Diameter (mm)	Post to Bearer Fixing (kN)
PLPH5-150 135x135mm	1.80	3.0	1.1	1.0	450	6
	2.10	2.7	0.8	1.0	450	6
	2.40	2.4	0.6	1.0	450	6
PLPH5-200 180x180mm	1.80	7.0	3.4	1.2	450	12
	2.10	6.3	2.6	1.2	450	6
	2.40	5.7	2.0	1.2	450	6
	2.70	5.2	1.6	1.2	450	6
	3.00	4.8	1.2	1.2	450	6
	3.30	4.3	0.9	1.2	450	6
PLPH5-250 220x220mm	1.80	11.7	5.9	1.5	600	12
	2.10	10.6	5.4	1.5	600	12
	2.40	9.7	4.4	1.5	600	12
	2.70	8.9	3.5	1.5	600	12
	3.00	8.2	2.8	1.5	600	12
	3.30	7.7	2.1	1.5	600	12
	3.60	7.2	1.6	1.5	600	12
PLPH5-300 260x260mm	2.20	16.9	8.6	1.7	600	12
	2.40	16.0	8.1	1.7	600	12
	2.70	14.7	6.9	1.7	600	12
	3.00	13.6	5.4	1.7	600	12
	3.30	12.6	4.1	1.7	600	12
	3.60	11.8	3.2	1.7	600	12
	3.90	11.1	2.5	1.7	600	12
	4.20	9.3	2.0	1.7	600	12

Note: The design parameters are specified in the design data page. For different parameters, refer to Prolam Online Specifier at specifier.prolamnz.com

These span tables apply only to Prolam products.

Span Tables




Table 12b

Prolam® Bracing Post Veranda/Carport - free standing supporting roof and ceiling PL12

Post Size	Post Height (m)	Maximum plan area per post (AP) (m^2)	Maximum face area per post (AF) (m^2)	Footing Depth (m)	Footing Diameter (mm)	Post to Bearer Fixing (kN)
PLP12H5-150 135x135mm	1.80	3.9	1.6	1.1	450	6
	2.10	3.5	1.2	1.1	450	6
	2.40	3.2	0.9	1.1	450	6
PLP12H5-200 180x180mm	1.80	9.2	4.7	1.3	450	12
	2.10	8.2	3.7	1.3	450	12
	2.40	7.5	2.9	1.3	450	6
	2.70	6.8	2.3	1.3	450	6
	3.00	6.3	1.8	1.3	450	6
	3.30	5.8	1.4	1.3	450	6
PLP12H5-250 220x220mm	1.80	15.4	7.8	1.6	600	12
	2.10	14.0	7.1	1.6	600	12
	2.40	12.7	6.4	1.6	600	12
	2.70	11.7	5.1	1.6	600	12
	3.00	10.8	4.0	1.6	600	12
	3.30	10.1	3.0	1.6	600	12
	3.60	9.4	2.4	1.6	600	12
PLP12H5-300 260x260mm	2.20	22.3	11.3	1.8	600	12
	2.40	21.0	10.6	1.8	600	12
	2.70	19.3	9.8	1.8	600	12
	3.00	17.9	7.8	1.8	600	12
	3.30	16.6	5.9	1.8	600	12
	3.60	15.5	4.6	1.8	600	12
	3.90	14.6	3.6	1.8	600	12
	4.20	13.3	2.9	1.8	600	12

Note: The design parameters are specified in the design data page. For different parameters, refer to Prolam Online Specifier at specifier.prolamnz.com

These span tables apply only to Prolam products.

Span Tables




Table 12c

Prolam® Bracing Post Veranda/Carport - attached to house supporting roof and ceiling - PL8

Post Size	Post Height (m)	Maximum plan area per post (AP) (m^2)	Maximum face area per post (AF) (m^2)	Footing Depth (m)	Footing Diameter (mm)	Post to Bearer Fixing (kN)
PLPH5-150 135x135mm	1.80	5.9	2.2	1.0	450	6
	2.10	5.3	1.6	1.0	450	6
	2.40	4.8	1.3	1.0	450	6
PLPH5-200 180x180mm	1.80	14.0	6.9	1.2	450	12
	2.10	12.5	5.1	1.2	450	6
	2.40	11.4	4.0	1.2	450	6
	2.70	10.4	3.2	1.2	450	6
	3.00	9.6	2.5	1.2	450	6
	3.30	8.6	1.9	1.2	450	6
PLPH5-250 220x220mm	1.80	23.5	11.9	1.5	600	12
	2.10	21.2	10.7	1.5	600	12
	2.40	19.4	8.9	1.5	600	12
	2.70	17.8	7.1	1.5	600	12
	3.00	16.5	5.6	1.5	600	12
	3.30	15.3	4.2	1.5	600	12
	3.60	14.3	3.3	1.5	600	12
PLPH5-300 260x260mm	2.20	33.9	17.1	1.7	600	12
	2.40	31.9	16.1	1.7	600	12
	2.70	29.4	13.8	1.7	600	12
	3.00	27.2	10.9	1.7	600	12
	3.30	25.3	8.2	1.7	600	12
	3.60	23.6	6.4	1.7	600	12
	3.90	22.2	5.1	1.7	600	12
	4.20	18.5	4.1	1.7	600	12

Note: The design parameters are specified in the design data page. For different parameters, refer to Prolam Online Specifier at specifier.prolamnz.com

These span tables apply only to Prolam products.

Span Tables




Table 12d

Prolam® Bracing Post Veranda/Carport - attached to house supporting roof and ceiling - PL12

Post Size	Post Height (m)	Maximum plan area per post (AP) (m^2)	Maximum face area per post (AF) (m^2)	Footing Depth (m)	Footing Diameter (mm)	Post to Bearer Fixing (kN)
PLP12H5-150 135x135mm	1.80	7.8	3.1	1.1	450	6
	2.10	7.0	2.3	1.1	450	6
	2.40	6.3	1.8	1.1	450	6
PLP12H5-200 180x180mm	1.80	18.4	9.3	1.3	450	12
	2.10	16.5	7.4	1.3	450	12
	2.40	14.9	5.7	1.3	450	6
	2.70	13.7	4.5	1.3	450	6
	3.00	12.6	3.6	1.3	450	6
	3.30	11.7	2.7	1.3	450	6
PLP12H5-250 220x220mm	1.80	30.9	15.6	1.6	600	12
	2.10	27.9	14.1	1.6	600	12
	2.40	25.5	12.7	1.6	600	12
	2.70	23.4	10.1	1.6	600	12
	3.00	21.7	8.0	1.6	600	12
	3.30	20.2	6.1	1.6	600	12
	3.60	18.9	4.7	1.6	600	12
PLP12H5-300 260x260mm	2.20	44.5	22.5	1.8	600	12
	2.40	41.9	21.2	1.8	600	12
	2.70	38.6	19.5	1.8	600	12
	3.00	35.7	15.6	1.8	600	12
	3.30	33.2	11.8	1.8	600	12
	3.60	31.1	9.2	1.8	600	12
	3.90	29.2	7.3	1.8	600	12
	4.20	26.6	5.9	1.8	600	12

Note: The design parameters are specified in the design data page. For different parameters, refer to Prolam Online Specifier at specifier.prolamnz.com


These span tables apply only to Prolam products.

Span Tables

Table 13

Prolam® Non-Bracing Post - attached to house supporting veranda roof and ceiling only

1. Post height is measured from ground level to top of roof beam.
2. Veranda or carport 2.0m or less and attached to the house, does not require bracing.
3. Refer to NZS3604:2011 section 9 for size of concrete footing to resist uplift.
4. For post sizes to roof that require bracing refer to separate tables.



Veranda Post		Maximum Post Height from Ground (m)	Maximum Supported Roof Area per Post (m^2)
PLPH5-100	88 x 88mm	2.4	16
PLPH5-125	112 x 112mm	3	27
PLPH5-150	135 x 135mm	3.6	39
PLPH5-200	180 x 180mm	4.2	50

Roof Area = Roof Width x Post Spacing / 2


Note: The design parameters are specified in the design data page. For different parameters, refer to Prolam Online Specifier at specifier.prolamnz.com

These span tables apply only to Prolam products.

Span Tables

Table 14

Prolam® Non-Bracing Post - attached to house supporting veranda or deck floor only



Post Height From Ground (m)		1.8	2.4	2.7	3.0	3.6	4.2
Deck Post		Maximum Supported Deck Area per Post (m^2)					
PLPH5-125	112 x 112mm	8	7.3	6.9	6.4	-	-
PLPH5-150	135 x 135mm	11.9	11.4	11	10.5	9.4	-
PLPH5-200	180 x 180mm	21.5	21.2	21	20.6	19.6	18.3
PLPH5-250	220x220mm	32.1	32.1	31.9	31.7	30.9	29.8
PLPH5-300	260x260mm	44.9	44.9	44.8	44.7	44.2	43.3

$$\text{Deck Area} = \frac{\text{Deck Width}}{2} \times \text{Post Spacing}$$

Note: The design parameters are specified in the design data page. For different parameters, refer to Prolam Online Specifier at specifier.prolamnz.com


These span tables apply only to Prolam products.

Span Tables

Table 15

Prolam® Non-bracing Post - attached to house supporting veranda deck floor and roof with ceiling

1. Tributary roof area must be equal to the tribtary floor area.
2. Post height is measured from ground level to floor bearer connection point.



Veranda Post		Post Height From Ground (m)	Maximum Supported Roof Area per Post (m²)
PLPH5-125	112 x 112mm	3.0	5.0
PLPH5-150	135 x 135mm	3.6	8.0
PLPH5-200	180 x 180mm	4.2	16.0
PLPH5-250	220 x 220mm	4.2	26.0
PLPH5-300	260 x 260mm	4.2	38.0

Roof Area = Roof Width x Post Spacing / 2

Note: The design parameters are specified in the design data page. For different parameters, refer to Prolam Online Specifier at specifier.prolamnz.com

These span tables apply only to Prolam products.

Fixings



Fixing to MCA Timber

Indirectly endorsed by BRANZ, Prolam recommends as a minimum, the specification and use of 304 stainless fasteners, nails and screws for any H3.2-H5 treated timber in all exterior and or exposed applications.

As stated in NZ3604 (4.4.4) Steel fixings and fastenings in contact with timber treated with copper based timber preservatives (H3.2 or higher) shall be as per table 4.1 and table 4.3 but shall also be a minimum of:


a. Type 304 stainless steel for fixings in contact with timber treated with Copper Azole, or Alkaline Copper Quaternary (ACQ) preservatives, where used in exposed or sheltered locations.

b. Hot-dipped galvanized for all other locations


If you specifically require a reduced durability period for bolted connections in non-structural situations such as fences and pergolas, we would still recommend referring to NZS3604 as a guide or consult with a building professional.



Prolam® Tapered Ceiling Beam Detail



ELEVATION AT END OF CEILING BEAM



SECTION THROUGH CEILING BEAM

This table applies only to Prolam products.

Prolam® Support for Bricks


When a Prolam lintel is installed over an opening in a wall with brick cladding, a steel angle lintel complying with E2/AS1 Paragraph 9.2.9 can be used to support the cladding weight. The Prolam lintel should then be designed to carry other structural loads—such as roof or floor loads—using the Prolam Specifier or span tables. If the Prolam lintel is required to support the weight of the cladding, specific engineering design is required.

The steel angle lintel shall:

a) Be protected against corrosion as in E2/AS1 Table 18D and to exposure zones outlined in NZS 3604.

b) Have a minimum seating into adjacent veneer of:
   i) 100 mm for spans up to, and including 2 m,
   ii) 200 mm for spans over 2 m.

c) Be sized in accordance with E2/AS1 Table 18E.




E1/AS2 Table 18D: Corrosion protection to lintels		
	316 or 316L or 304 [2] stainless steel or 600 g/m² galvanising on mild steel plus duplex coating [1]	600 g/m² galvanising on mild steel [1] or 300 g/m² galvanising on mild steel plus Duplex coating [1]
Zone B	Yes	Yes
Zone C	Yes	Yes
Zone D	Yes	

1) To AS/NZS 2699.3
2) 304 stainless steel will exhibit greater levels of surface rusting than 316 stainless steel, especially where not exposed to rain washing.


E2/AS1 Table 18E: Masonry veneer lintel sizes (minimum)						
Span of lintel (m) up to:	**Maximum thickness of masonry veneer (mm)**					
	70			90		
	Maximum height of veneer supported (mm)					
	350	700	2000	350	700	2000
0.8	60 x 60 x 6 L	61 x 60 x 6 L	62 x 60 x 6 L	60 x 80 x 6 L	61 x 80 x 6 L	80 x 80 x 6 L
2.0	60 x 60 x 6 L	61 x 60 x 6 L	62 x 60 x 6 L	60 x 80 x 6 L	61 x 80 x 6 L	81 x 80 x 6 L
2.5	61 x 60 x 6 L	80 x 80 x 6 L	81 x 80 x 6 L	80 x 80 x 6 L	81 x 80 x 6 L	82 x 80 x 6 L
3.0	80 x 80 x 6 L	81 x 80 x 6 L	125 x 75 x 6 L	81 x 80 x 6 L	80 x 80 x 8 L	90 x 90 x 10 L
3.5	80 x 80 x 6 L	81 x 80 x 6 L	126 x 75 x 6 L	80 x 80 x 8 L	90 x 90 x 10 L	125 x 75 x 10 L
4.0	80 x 80 x 8 L	125 x 75 x 6 L	125 x 75 x 10 L	80 x 80 x 10 L	125 x 75 x 6 L	150 x 90 x 10 L
4.5	125 x 75 x 6 L	125 x 75 x 10 L	-	125 x 75 x 6 L	125 x 75 x 10 L	-
4.8	125 x 75 x 6 L	125 x 75 x 10 L	-	125 x 75 x 6 L	125 x 75 x 10 L	-

Prolam® Post Fixings




NOTE -
(1) Capacity 12.2 kN for 1 bracket.
(2) Capacity 25.5 kN for 2 brackets.

(A)



NOTE -
(1) Capacity 6.8 kN for 1 bracket.
(2) Capacity 13.7 kN for 2 brackets.


(B)



NOTE -
Capacity 6.8 kN.

(C)

Unless otherwise stated, all dimensions are in mm.




BEAM FIXING


(D)

Uplift capacity
2 / M12 bolts – 7.8 kN
2 / M16 bolts – 12.0 kN


Prolam® Post Fixings



SCARF JOINT AT POSTS




BEAM SPLICE FOR 180x180 OR LARGER POSTS




SCARF JOINT FOR 190 BEAMS

Not suitable for M16 bolts




SCARF JOINT FOR 240 OR LARGER BEAMS

Prolam® Corner Post Fixings




ELEVATION

Characteristic Capacities for uplift (2/M12 bolts)
14.0 kN - dry (sheltered) use
9.8 kN - wet (exposed) use



PLAN



ELEVATION

Characteristic Capacities for uplift (2/M16 bolts)
21.5 kN - dry (sheltered) use
15.0 kN - wet (exposed) use


Post embedded into 450 dia x1.2m deep concrete footing will give 20kN uplift resistance in clay soils. Otherwise refer to section 9 of NZS3604:2011 for post footing requirements to resist uplift.

CORNER POST - LINTEL CONNECTION DETAIL

Prolam PLX20® Fixings


A1. RAFTER/TRUSS DIRECT CPC80 FIXING


- For use only with the MiTek 16KNTTP Kit.
- Use 4 of the 8 provided Type 17-14g x 75 mm screws (2 each side) and discard the remainder.
- The choice of fixing holes to the rafters should be offset to avoid interfering with the opposite side fixings.



Characteristic Strength (kN/Pair)	ULS Capacity (kN/Pair)
16	11.2


B1. RAFTER/TRUSS CPC80 FIXING WITH DOUBLE TOP PLATES






Characteristic Strength (kN/Pair)	ULS Capacity (kN/Pair)
16	11.2


B2. RAFTER/TRUSS CPC80 FIXING WITH SINGLE TOP PLATE



Characteristic Strength (kN/Pair)	ULS Capacity (kN/Pair)
16	11.2


C1. RAFTER/TRUSS CPC40 FIXING WITH DOUBLE TOP PLATES





Characteristic Strength (kN/Pair)	ULS Capacity (kN/Pair)
8	5.6


C2. RAFTER/TRUSS CPC40 FIXING WITH SINGLE TOP PLATE



Characteristic Strength (kN/Pair)	ULS Capacity (kN/Pair)
8	5.6


Prolam PLX20® Fixings

G1. RAFTER/TRUSS CYCLONE STRAP FACE FIXING




Characteristic Strength (kN)	ULS Capacity (kN)
12.0	9.6

H1. RAFTER/TRUSS CEILING TIE FACE FIXING




Characteristic Strength (kN/Pair)	ULS Capacity (kN/Pair)
10.5	8.4

I1. RAFTER/TRUSS DIAGONAL CLEAT N21 FACE FIXING




Characteristic Strength (kN/Pair)	ULS Capacity (kN/Pair)
20.0	16.0

J1. RAFTER/TRUSS CEILING & PURLIN HANGER FACE FIXING




Characteristic Strength (kN/Pair)	ULS Capacity (kN/Pair)
-	5.0

K1. RAFTER/TRUSS Z-NAIL FACE FIXING



Characteristic Strength (kN/Pair)	ULS Capacity (kN/Pair)
3.2	2.5

L1. RAFTER/TRUSS MULTIGRIP FACE FIXING



Characteristic Strength (kN/each)	ULS Capacity (kN/each)
4.0	3.2

Prolam® Stud Requirement Table

Construction Specifications


Walls are to be fully lined on at least one face. Full bearing on top plate (i.e. no eccentric loading).

Bearing Reaction	Stud Requirement for Concentrated Loads	
	Stud Height	**Requirements**
Bearing reaction up to & including 10kN	2400	Refer to NZS 3604:2011
	2700	
	3000	
	Stud Height	**Stud Required**
Bearing reaction up to & including 20kN	2400	PL8H5-100 90 x 90
	2700	PL8H5-100 90 x 90
	3000	PL8H1-150 140 x 90
	Stud Height	**Stud Required**
Bearing reaction up to & including 30kN	2400	PL8H1-150 140 x 90
	2700	PL8H1-150 140 x 90
	3000	PL8H1-200 190 x 90

* **Note** The stud requirement for 20 kN & 30 kN bearing reactions can be applied to external walls as well. Reactions over 30kN will require specific design.

These span tables apply only to Prolam products.

Prolam® Holes in Laminated Timber



Beam Depth (d) (mm)	Max Hole Dia. (d) (mm)	Min. Edge Dist. (t) (mm)	Min. Edge Dist. (ls) (mm)
140	20	50	230
190	25	70	310
240	35	85	390
290	45	105	470
315	50	115	510
360	55	130	580
405	60	145	655
450	70	160	725
495	75	175	800
540	80	190	870
595	90	210	960

No holes in cantilever joist Circular Holes are only Permitted.

This table applies only to Prolam products.

FAQs

Why should I use Prolam Glulam instead of steel?

Here are just a few reasons:

- Easier and lighter to handle and fix
- Friendlier on the environment - stores carbon rather than emitting it
- Uses NZ's only renewable construction material - plantation timber
- Uses 14 times less energy to produce than equivalent steel beam
- Superior Fire Resistance compared to steel
- Lower maintenance - Glulam does not rust or corrode
- Cost effective - no boxing in or covering as with steel beams
- Appearance - natural warmth and beauty of timber cannot be reproduced in steel
- Will not buckle or distort in response to temperature changes
- Direct fixing of plates, joists and other connections is much easier

Why should I use Prolam Glulam instead of solid timber?

Because Prolam Glulam is manufactured from selected grade, kiln-dried material it is more stable than a sawn timber beam of the same section. The tendency of large section sawn timber to twist, split and shrink is greatly minimised in Prolam. A Prolam beam can reduce the overall section of members up to 40% compared to unseasoned timber, as they are pretensioned.

What type of quality assurance comes with Prolam Glulam Beams?

All Prolam Glulam is manufactured to comply with the Australia and New Zealand Standard AS/NZS1328 and AS5096 - Glue Laminated Structural Timber A.

Can Prolam Glulam beams be used in exterior situations?

Yes. Prolam posts and beams treated to H3 or H5 may be used in exterior situations provided that they are finished with a paint or staincoating. Prolam beams and posts should always be painted with light colours or dark colours with light reflectance value (LRV) of greater than 45%. Colours with an LRV of 45% or less are not recommended, as they can absorb heat which may result in timber distortion and cracking. Because Prolam Glulam is chemically inert it is ideal for corrosive atmospheres such as swimming pools, marine structures, fertilisers and scouring plants where steel is subject to rust and corrosion.

What finish should I ask for on my beams?

If your beam is going to be used in a situation where appearance is important such as house interiors, halls etc - Visual Appearance Grade A should be specified. If you require a sanded finish, please specify. Non visual grade is intended for use where the product is not seen and occasional chips and voids are acceptable.

Are H5 Laminated Posts certified for in ground use? Yes. Prolam is leading the way with H5 laminated structural in-ground posts. Codemarked for NZBC Compliance in B1 and B2, it means you can use Prolam in-ground posts with more confidence than ever.

What is the difference between GL and PL grade?

The GL prefix is a reference to the old term "Glulam", where the PL is the prefix for branded "Prolam" structural timber.

FAQs - continued

Will MCA treated Prolam cause corrosion on galvanised fixings?

While this may be a problem with solid unseasoned timber, Prolam does not act in the same way. Because all Prolam is manufactured from material that is kiln dried after treatment, the treatment salts are thoroughly fixed into the timber. They will therefore not subsequently leach out or affect galvanised fixings. For additional protection it is recommended that bolts be greased before inserting into MCA treated Prolam beams that are exposed to the weather.

How long should I keep the wrapping on?

Wrapping of Prolam beams is primarily to protect them from marking during handling and transport. This is not designed to be a waterproof protection. Once on-site water can often get in under the wrapping and cannot get out. Wrapping should be slit to provide drainage. Wrapping can be left on Prolam beams for as long as possible (even during construction) to protect against accidental marking. Also be aware that partial removal of wrapping to access connections may cause patches of discolouration by exposure to weather.

Can finished Prolam beams be re-cut and drilled?

Any cutting, drilling or slotting that exposes unsealed timber must be protected with an application of appropriate weather or treatment sealer. Avoid cut-outs, rebating or drilling in the top and bottom edges of Prolam beams. These could cause serious weakness in tension and compression areas. Consult the manufacturer or designer first.

Do splits along glue lines mean delamination has occurred?

Actual delamination is a failure in the laminating process. While an opening along a glue line may be indicative of delamination there are other more common causes. Typical checking that occurs in large section timber in response to moisture variation will most naturally occur in Prolam along a glue line where the natural continuation of the timber fibres is interrupted. This is often mistaken for delamination. (Ref to Timber Design Journal pg 39&40)

How serious are checks and why do they appear?

Surface checking and splits occur as timber is allowed to absorb moisture then dries out in response to environmental changes. Surface fibres are more severely exposed to these changes than the inner core and as a result of the movement in these fibres as they dry and shrink, surface splits may occur. Changes in atmospheric conditions will affect the appearance and disapperarance of these checks. The effect of surface checks are superficial only and do not usually have any effect on the structural performance of the Prolam.

How can these checks be minimised?

Prolam® beams are provided with a sealer coating if requested, which controls the ingress of moisture into the timber, and is done before the beams leave the factory. If the beams are exposed to the weather for a greater period that 8-10 weeks, a further coating should be applied. Consult our painting instructions for permanent sealing requirements.

FAQs - continued

Where can H1.2 treatment be used?

Prolam treated to H1.2 is only suitable to be used in the building envelope as in NZS3604:2011.

What is the difference between Visual and Non-Visual grades?

Prolam Visual is made from visually selected sharts that are then finger jointed together into a long length and laminated into the required beam. This grade is recommended for use in highly visual areas and when a paint or stain quality finish is required. Prolam Non-Visual is made up from stress graded timber and is not visually graded. The non-visual grade is recommended where the beams are not seen. [Refer to Prolam finishes]

Why is bandsawn finished smaller than standard?

Bandsawn finished Prolam posts and beams are 6mm smaller than standard, because we have to cut the bandsawn finish into the beams after they are made. Use the Prolam Online calculator to specify this product.

What is the fire rating of Prolam?

The BRANZ appraisal states a charring rate from the table below:

Density (kg/m³)	Charring Rate (mm/min)
400	0.75
500	0.70
600	0.65

It is recommended that this simplified table of data derived from "White's" model and should be adopted for design of fire resistant timber structures in New Zealand. Prolam density is 550 Kg/m³.

Can you cut drill, machine Prolam after manufacturing?

Yes, because Prolam is pretreated before laminating, all pieces are fully treated, so any cutting etc. does not need apaint on treatment applied to the cut portion. However, any cuts to be sealed as per sealing specifications

Can I buy direct from Prolam?

All Prolam products are supplied through the main timber merchants nationwide, as well as many timber specialist stores.

What is the difference between PL8 and PL12?

PL8 is made from SG8 timber, whereas PL12 is made from PL12 timber. PL12 has higher strength and stiffness properties and enables you to achieve bigger spans with larger loaded dimensions.
For a similar span and loaded dimension, a PL12 can offer a smaller section where the space is limited or aesthetics are important.

Does cutting into or notching out a Prolam post or beam affect the treatment?

No this does not. Each laminate used for H3.2 or H5 products is treated right through before it is laminated. This gives a Prolam post or beam around 50% more treatment than a solid timber post or beam which can only be treated from the outside. End grain and/or cut ends and joins should be sealed to prevent any ingress of moisture.

Can I request samples?

Please email info@prolamnz.com if you would like to request samples.

FAQs - Prolam Specifier

What is the classification of timber to be used for joint design as per table 4.1 of NZS3603?

The classification for Prolam products would be J5.

What is the tributary joist & bearer span?

The tributary area is a loaded area that contributes to the load on the member supporting that area. On the Prolam Specifier under each non-bracing calculator, the diagram shows how to calculate this.

Where is the bracing posts chart on the Specifier?

Under http://specifier.prolamnz.com/resources refer to the document 'Prolam Bracing Posts'

Should I go by absolute deflection or residual deflecton?

Depending on the allowance for deflection below the horizontal line, the residual deflection is long term deflection below horizontal after pre-camber and is the recommended value for typical designs. The 'absolute deflection is the maximum beam movement. After selecting 'calculate' these notes are located below the list of products that suit the design.

Scan QR Code for additional FAQ's online
https://www.prolamnz.com/technical/faq

Building Product Information

Names and descriptions of products

Names and descriptions can be found on pages 5 – 17 of the Prolam structural timber guide.

Product Identifier

Product identifiers can be found on pages 5 – 17 of the Prolam structural timber guide

Legal Trading name

Prowood Ltd is the Legal and trading name of the Prolam products

Relevant Building Code Clauses

Clause B1 Structure: Performance B1.3.1, B1.3.2 and B1.3.4 for relevant physical conditions of B1.3.3 (a) (b) (g) (h) and (j) [i.e self-weight, imposed gravity loads arising from use, snow, wind and impact]

Clause B2 Durability: Performance B2.3.1 (a) 50 years

Clause F2 Hazardous Building Materials: Performance F2.3.1

Design requirements

Page 48

Installation Requirements

Pg 27

Maintenance Requirements

Pg 29

Warning or Bans

Prolam products are not subject to any warnings or bans



> The ease of using the Prolam program makes specifying a quality product to match clients expectations a no brainer.
>
> Shaun, ITM Blenheim

> We see a number of the Prolam products as being the perfect partner in achieving great architecture with a sustainable solution.
>
> Mark, Bishop Architecture

Licensed Builders Practitioners Details

LBP Points Here

This Prolam® Builders Booklet will give you LBP points if you record reading it as your **Skills Maintenance Activity.**

- Log onto **https://lbp.dbh.govt.nz/OnlineAccount/Login.aspx** to set up your user account, or if you are already set up, log in here to record your learning.
- Or you can record your learning by making a note in your Diary.
- One hour of learning = 1 point
- Be sure to write down how and what you learnt and include the date and the time taken.
- You can also go to our web site and download a Q & A sheet as a record of learning.



Record of Skills Maintenance Form

Return this form with your annual licence fee

Full Name

LBP Number

Enter details of your Skills Maintenance. Remember to include all of your activities, and include additional pages if needed

Activity

Date Completed Hours

Details of Activity

Activity

Date Completed Hours

Details of Activity

Activity

Date Completed Hours


Details of Activity

Declaration

I declare this is a true record of my skills maintenance activities. I understand that the Registrar can ask to see my personal skill maintenance records that support this claim. I understand that it is an offence under the Building Act 2004 to provide incorrect or misleading information.

Signature _____ Date _____

Please Post to: **The Registrar**
Ministry of Business, Innovation and Employment,
PO Box 50041, Porirua 5240



Planning a project?

Our team of experts are ready to assist.

Register to our Online Specifier **specifier.prolamnz.com**

Prolam®

Engineered Laminated Timber

03 526 7436

info@prolamnz.com

prolamnz.com