



**Standard Carpets ind llc**  
**Mr. Sahil Passi**  
**P.O. Box No. 490014 Dubai Industrial Park**  
**DUBAI UAE**  
**Verenigde Arabische Emiraten**

**Your notice of**  
 14-02-2019

**Your reference**

**Date**  
 26-03-2019

**Analysis Report 19.00965.01**

Required tests :

**AS ISO 9239-1 (2003)**

Identification number	Information given by the client	Date of receipt
T1903645	FAST FORWARD	14-02-2019



**Kristina De Temmerman**  
 Order responsible

This report may be reproduced, as long as it is presented in its entire form, without written permission of Centexbel.  
 The results of the analysis cover the received samples. Centexbel is not responsible for the representativeness of the samples.  
 In assessing compliance with the specifications, we did not take into account the uncertainty on the test results.

**Reference: T1903645 - FAST FORWARD**

**Reaction to fire tests for floorings - Determination of the burning behaviour using a radiant heat source**

Date of ending the test	12-03-2019
Standard used	AS ISO 9239-1 (2003)
Deviation from the standard	-
Conditioning	23°C, relative humidity 50% Minimum 14 days or until constant mass is achieved

The test results relate to the behaviour of the test specimens of a product under the particular conditions of the test: they are not intended to be the sole criterion for assessing the potential fire hazard of the product in use.

**Test specimen**

Substrate	Fibre cement board - density (1800 ± 200) kg/m <sup>3</sup>
Mounting	Loose-laid
Specimens have not been cleaned	
Joint	At 25 cm and 75 cm

### Radiant heat flux

Test	flame spread distance (cm)				extinguishment		heat flux (kW/m <sup>2</sup> )	
	10 min	20 min	30 min	extinguishment			30 min*	extinguishment**
<b>width</b>								
<b>1</b>	21	24	24	24	15 min	50 s	8,8	8,8
<b>length</b>								
<b>1</b>	20	24	24	24	17 min	20 s	8,8	8,8
<b>2</b>	21	24	24	24	16 min	0 s	8,8	8,8
<b>3</b>	22	24	24	24	16 min	10 s	8,8	8,8
<b>average</b>							8,8	8,8

\* Heat flux at the time of 30 minutes

\*\* Heat flux at the time of flame extinguishment

### Smoke production

The following parameters are measured :

- maximum light attenuation (%) after 30 min and flame extinguishment
- total light attenuation (%min) after 30 min and flame extinguishment

Test	maximum light attenuation (%)		total light attenuation (%min)	
	30 min	extinguishment	30 min	extinguishment
<b>width</b>				
<b>1</b>	35	35	133	133
<b>length</b>				
<b>1</b>	28	28	123	123
<b>2</b>	33	33	160	147
<b>3</b>	34	34	163	155
<b>average</b>			149	142