



AAB Acoustic Blanket

GreenStuf® AAB ACOUSTIC BLANKET is a range of 100% polyester acoustic insulation products designed for reducing and controlling reverberated noise in building interiors. AAB is ideally suited for use as an absorber behind acoustic panels and ceiling systems.

GreenStuf® AAB is available in a range of densities and performance options. AAB is supplied as lofted white or black insulation panels /sheets measuring 2400mm x 1200mm.



Applications

GreenStuf® AAB has been engineered to maximize sound absorption for the control of reverberated noise in building interiors. AAB is ideal for managing noise in theatres, studios, auditoriums, halls, offices, retail and indoor swimming pool complexes. AAB can also be used in marine applications, as acoustic baffles, acoustic infill for silencers and louvres, and insulation for Original Equipment Manufacturers (OEM).

Technical

BCA Compliance: GreenStuf® insulation when installed in accordance with the manufacturer’s instructions will satisfy the 50 year durability criteria for minimum design life as set out in the ABCB guidance document Durability in Buildings 2006 (Section 2.4).

Durability: GreenStuf® has a 50 Year Durability Warranty.

Vermin: GreenStuf® is naturally resistant to insect and vermin attack.

Product Format: AAB is available as standard 2400mm x 1200mm sheets, in black and white. Custom sizes, grey colour blends and self-adhesive backed options are available with minimum order quantities on request.

The product Nominal Thickness is the off-line manufactured thickness. Packaging, storage and handling may affect the “out of the pack” thickness. This is not considered a manufacturing fault. If thickness is critical to a particular installation please discuss your requirements with your Autex Account Manager.

Moisture: GreenStuf® is not affected by moisture. Exposure to an atmosphere of 50°C at 90% relative humidity for four days showed moisture absorption by weight of less than 0.03%.

Hazardous Building Materials: GreenStuf® is non hazardous.

VOC Emission Safe:

VOC concentration: 0.01 mg/m³ (7 days).

GECA/GreenGuard Limit: 0.25 mg/m³ (7 days).

Cetec Pty Ltd (Report:RCV080408)

Non-Corrosive: GreenStuf® polyester is pH7.8 (pH7 is neutral).

Non-Toxic, Non-Allergenic, Non-Irritant: There are no known hazards with the use or handling of GreenStuf® polyester.

MSDS: Material Safety Data Sheets (MSDS) are available on request from your Autex Representative or by visiting our website: www.autex.com.au

PRODUCT	EX-STOCK SUPPLY	NOMINAL THICKNESS (mm)	NRC	Est. R-VALUE (m ² /kw)	PACK SIZE	m ² /PACK
AAB 14-25		25mm	0.50	R0.48	1200mm x 2.4m x 10 Sheets	28.8m ²
AAB 25-25	✓	25mm	0.55	R0.61	1200mm x 2.4m x 10 Sheets	28.8m ²
AAB 35-25	✓	25mm	0.70	R0.68	1200mm x 2.4m x 10 Sheets	28.8m ²
AAB 48-25		25mm	0.75	R0.73	1200mm x 2.4m x 10 Sheets	28.8m ²
AAB 14-50	✓	50mm	0.75	R0.95	1200mm x 2.4m x 5 Sheets	14.4m ²
AAB 35-50	✓	50mm	0.90	R1.36	1200mm x 2.4m x 5 Sheets	14.4m ²
AAB 48-50		50mm	0.90	R1.47	1200mm x 2.4m x 5 Sheets	14.4m ²
AAB 20-75		75mm	0.85	R1.68	1200mm x 2.4m x 3 Sheets	8.6m ²
AAB 35-75		75mm	1.05	R2.03	1200mm x 2.4m x 3 Sheets	8.6m ²
AAB 48-75		75mm	1.05	R2.20	1200mm x 2.4m x 3 Sheets	8.6m ²
AAB 20-100	✓	100mm	0.95	R2.24	1200mm x 2.4m x 2 Sheets	5.7m ²
AAB 40-100		100mm	1.05	R2.64	1200mm x 2.4m x 2 Sheets	5.7m ²
AAB 48-100		100mm	1.10	R2.81	1200mm x 2.4m x 2 Sheets	5.7m ²

Installation: GreenStuf® AAB should ideally be installed with the textured/patterned surface exposed to the sound source. AAB can be fixed to wall and ceiling substrates using a contact type adhesive (ADOS F2) and/or mechanical fixings such as insulation anchors. Additional information and advice is available from your Autex Representative or by visiting our website: www.autex.co.nz

Non-Flammable: GreenStuf® is classified non-flammable.

Fire ratings:

ISO 9705: 1993

Australian Group Number: Group 1

SMOGR_{RC}: less than 100m²/s²

Test Number: FAR4045

AS1530.3

Ignitability Index (0-20) 0

Heat Evolved Index (0-10) 0

Spread of Flame Index (0-10) 0

Smoke Developed Index (0-10) 3

APL Report 98055

IEC 60695-11-5 (Downlight Fire Test Standard)

GreenStuf® has been tested and certified non-flammable and complies with the requirements of IEC 60695-11-5.

Certificates available from our website.

Specification & Substitution: Autex specification documents are available from our website (www.autex.com.au). Substitution of any products should not be accepted and we recommend this be made clear in all specification and tender documents.

The performance and design of AAB has been engineered to supply a tested and proven sound control system. Substitution of any specified components in a sound control system can significantly compromise the system performance.

Accept NO substitutions.

Take Back Programme: Autex will gladly recycle used, uncontaminated GreenStuf® insulation to help keep it out of landfill. For more information on recycling GreenStuf® contact Autex on freephone 1800 678 160.

ISO Standards: Autex is committed to Quality and Environmental best practice through our ISO 9001 & ISO 14001 certified Quality and Environmental Management Systems.

Acoustic and Thermal Performance: All AAB acoustic and thermal performance testing has been carried out in a laboratory environment. On-site results could vary depending on the system design, product handling and quality of the installation. For service and advice, please contact your Autex Representative or Autex Customer Services on 1800 678 160.

Environmental: All Polyester insulation products as manufactured by Autex Pty Ltd and marketed under the name GreenStuf and is produced using 100% Polyester fibre without the need for any binders or adhesives. Our products are manufactured with up to 85% recycled fibre. These products do not contain nor produce any ozone depleting substances or gases. Our products are rated as low VOC and no VOCs are used during the manufacturing process.

Autex Polyester Insulation Products are manufactured under ISO 9001 quality and ISO14001 environmental managed systems that include zero waste policies as well as extended producer responsibility policies. All of our products are fully recyclable and have low embodied energy. Autex Polyester insulation products have been awarded Good Environmental Choice Australia status and have been fully verified by Ecospecifier. They provide maximum credit for GreenStar rated projects.

PRODUCT	DENSITY (kg/m ³)	NOMINAL THICKNESS (mm)	WEIGHT (gsm)	SOUND ABSORPTION — FREQUENCY (Hz)						
				125	250	500	1000	2000	4000	NRC
AAB 14-25	14	25mm	350	0.13	0.29	0.48	0.62	0.69	0.65	0.50
AAB 25-25	25	25mm	625	0.15	0.30	0.50	0.65	0.75	0.75	0.55
AAB 35-25	35	25mm	875	0.10	0.38	0.64	0.83	0.88	0.84	0.70
AAB 48-25	48	25mm	1200	0.15	0.42	0.73	0.92	0.96	0.90	0.75
AAB 14-50	14	50mm	700	0.29	0.54	0.78	0.82	0.80	0.76	0.75
AAB 35-50	35	50mm	1750	0.29	0.68	1.01	1.01	0.97	0.95	0.90
AAB 48-50	48	50mm	2400	0.30	0.55	0.90	0.95	0.95	0.95	0.90
AAB 20-75	20	75mm	1500	0.35	0.60	0.85	0.95	0.90	0.95	0.85
AAB 35-75	35	75mm	2625	0.38	0.95	1.16	1.07	0.98	0.96	1.05
AAB 48-75	48	75mm	3600	0.40	0.80	1.15	1.10	1.05	1.05	1.05
AAB 20-100	20	100mm	2000	0.50	0.85	1.00	0.95	0.95	1.00	0.95
AAB 40-100	40	100mm	4000	0.45	1.05	1.15	1.05	1.05	1.05	1.05
AAB 48-100	48	100mm	4800	0.88	1.14	1.10	1.03	1.03	0.98	1.10

AUTEX



Autex Pty Ltd - Melbourne
166 Bamfield Rd,
PO Box 5099,
West Heidelberg, Melbourne,
VIC 3081 Australia
Phone +61 3 9457 6700
Fax +61 3 9457 1020

Freephone 1800 678 160
www.autex.com.au

Autex Pty Ltd - Perth
195 Bank St,
East Victoria Park,
Perth, WA 6101
Australia
Phone +61 8 9355 1911
Fax +61 8 9355 1032

www.autex.com.au

Autex Pty Ltd - Sydney
16 Bushells Place,
Wetherill Park,
Sydney, NSW 2164
Australia
Phone +61 2 9756 3122
Fax +61 2 9756 3165

www.autex.com.au

Autex Pty Ltd - Queensland
7-11 Lancashire Street,
Acacia Ridge,
QLD 4110,
Australia
Phone +61 7 3712 4400
Fax +61 7 3712 4466

www.autex.com.au



FORMAN
BUILDING SYSTEMS